

AMENDMENT NO. 1 SEPTEMBER 2007
TO
IS 11057 : 1984 SPECIFICATION FOR
INDUSTRIAL SAFETY NETS

(First Revision)

(Page 3, clause 1.1) — Substitute the following for the existing:

'This standard prescribes the requirements of industrial safety nets made from man-made fibres and designed to catch personnel and/or debris falling whilst work on high rise buildings, flyovers, roads/expressways, chimneys, industrial equipment installation like conveyors and structural work of shipbuilding is carried out.'

(Page 4, clause 3.1) — Substitute the following Notes for the existing:

NOTES

1 Strong sunlight can cause weakening of the fibres, but it is unlikely to penetrate beneath the surface. An ultra-violet stabilizer should be incorporated in the fibres and unnecessary exposure should be avoided.

2 The safety nets and the nettings from which the safety nets are made shall be heat set so that slippage of knots and/or joints may be avoided. While heat setting the nettings/nets, care should be taken that the heat transfer adequately tightens the knots. The knots should not change position by more than 10 percent (average) when a load of 20 percent of Mesh Breaking strength is applied after installing a mesh on tensile testing machine as defined in ISO 1806. The average should be calculated over readings of 3 meshes at all 4 joints/knots of the mesh.

3 Net shall be made from man-made fibre ropes and braided/plaited cords.'

(Page 5, clause 4.2) — Substitute the following for the existing:

'Nets shall be made with a square or diamond mesh and the length of the mesh side shall not be greater than 10 cm with a tolerance of ± 3 percent except for length of mesh side 10 cm. In case of mesh size 10 cm the tolerance shall be -3 percent.'

(Page 5, clause 5.1) — Insert the following Note at the end of the clause:

'NOTE - A safety net made from braided/plaited cords is unlikely to unravel when used in the mesh cord.'

Amend No. 1 to IS 11057 : 1984

(Page 7, clause 7.2) — Add the following after (d):

'e) Length of the mesh side.'

(TX 9)

Reprography Unit, BIS, New Delhi, India