

AMENDMENT NO. 1 DECEMBER 2013
TO
IS 11092 : 2001 IRON ORE PELLETS FOR DIRECT
REDUCTION PROCESSES

(Second Revision)

(Page 1, clause 4.1, line 1) — Substitute the following for the existing:

‘The iron ore pellets shall conform to the following chemical analysis (on dry basis):’

(Page 2, clause 10) — Substitute the following for the existing:

‘Tumbler index of iron ore pellets shall be 94 percent minimum on +6.3 mm and 5 percent Maximum on - 0.5 mm, when determined in accordance with IS 6495.’