

AMENDMENT NO. 1 AUGUST 2010
TO
IS 11093 : 2001 IRON ORE LUMPS FOR DIRECT
REDUCTION PROCESSES — SPECIFICATION

(Second Revision)

(Page 1, clause 2) — Substitute 'IS 9660 : 2001 Method for determination of softening — Melting characteristics of iron ore lumps/pellets/sinter (*first revision*)' for 'IS 9660 : 1980 Guidelines for determination of softening characteristics of iron ore pellets' and 'IS 10823 : 1994 Methods of determination of thermal degradation index (TDI) and reduction degradation index (RDI) of iron oxides: lump ore, sinter and pellets (*first revision*)' for 'IS 10823 : 1984 Method for determination of thermal degradation index (TDI) and reduction degradation index (RDI) of iron oxides: lumps ores, sinter and pellets'.

[Page 1, clause 4.1, tabular matter, Fe (Total)] — Substitute '65.0, *Min*' for '66.0 *Min*'.

[Page 1, clause 4.1, tabular matter, $\text{SiO}_2 + \text{Al}_2\text{O}_3$] — Substitute '5.0, *Max*' for '4.0, *Max*'.

[Page 1, clause 4.1, tabular matter, Total of Pb, Zn, Cu, Sn, Cr and As] — Substitute '0.01, *Max*' for '0.02, *Max*'.

(Page 2, clause 5.1, tabular matter, *For Coal Based Size only*) — Substitute the following for the existing:

<i>'Size</i>	<i>For Coal Based</i>
+ 30 mm	Nil
+ 5-20 mm	90 %, <i>Min</i>
+ 20-25 mm	5 %, <i>Max</i>
– 5 mm	5 %, <i>Max</i>

(Page 2, clause 5.1, tabular matter, *For Gas Based Size* '+31 mm') — Substitute '5%' for 'Nil'.

(MTD 30)