

**AMENDMENT NO. 2 NOVEMBER 1994
TO
IS 11197 : 1985 SPECIFICATION FOR MONOAXIALLY
ORIENTED POLYPROPYLENE TAPES**

(*Page 4, clause 4.2*) — Substitute the following for the existing matter:

'The tenacity of the tape shall not be less than 40.5 g/tex (4.5 g/denier).'

(*Page 4, clause 4.3*) — Substitute the following for the existing matter.

'The elongation of the tape at the point of rupture shall not be less than 15 percent.'

(*Page 4, clause 4.5*) — Substitute the following for the existing matter.

'The finished width of the tape shall be as agreed to between the buyer and the seller or as declared. However, the finished width shall not exceed 5.0 mm and shall be subject to a tolerance of ± 5 percent on agreed or declared width.'