

AMENDMENT NO. 1 APRIL 2008
TO
IS 11284 : 1985 METHOD OF ROTARY TUBE TEST FOR IRON BEARING
MATERIALS FOR THE MANUFACTURE OF SPONGE IRON/DIRECT REDUCED
IRON (DRI)

(Page 3, clause 2.1, line 2) — Substitute '5-20 mm' for '6-20 mm'.

(Page 3, clause 2.1, line 3) — Substitute '3 mm' for '1 mm' and '3 - 15 mm' for '1 - 15 mm'.

(Page 3, clause 2.1, line 4) — Substitute '3 - 6 mm' for '1 - 6 mm'.

(Page 3, clause 2.1, line 7) — Substitute 'relevant parts of IS 1493*' for 'IS : 1493 - 1959*'.

(Page 3, clause 3.1, line 2) — Substitute 'IS 460 (Part 1) : 1985' for 'IS : 460 (Part 1) - 1978' and 'IS 460 (Part 2) : 1985' for 'IS : 460 (Part 2) - 1978'.

(Page 3, footnote marked ‡) — Substitute '(third revision)' for '(second revision)'.

(Page 3, clause 4.1, last sentence) — Substitute the following for the existing:

'The rotary tube is provided with arrangement of rotating it at a variable speed of 3-27 rev/min (normally operated at constant speed of 8 rpm) and admitting inert gas during the cooling period.'

[Page 4, clause 5.1(a), Ore size] — Substitute '5 - 20 mm' for '6 - 20 mm'.

[Page 4, clause 5.1(a), Coal size] — Substitute '3-15 mm' for '1-15 mm'.

(Page 4, clause 5.2.1) — Add the following at the end of the last sentence: 'or retained in the furnace'.

(Page 4, clause 5.2.2) — Substitute 'IS 1607 : 1977*' for 'IS : 1607 - 1960*'.

(Page 4, footnote marked *) — Substitute 'Methods for dry-sieving (first revision)' for the existing.

Amend No. 1 to IS 11284 : 1985

(Page 5, clause 6.1.1) — Substitute 'IS 10823 : 1994*' for 'IS : 10823-1984*'.

(Page 5, footnote marked *) — Add '(first revision)' at the end.