

AMENDMENT NO. 3 AUGUST 2024
TO
IS 11329 : 2018 FINNED TYPE HEAT EXCHANGER FOR ROOM AIR CONDITIONER
(First Revision)

(Page 4, Clause **6.2.1.5**) — Substitute the following for the existing:

‘6.2.1.5 Brazing material selection

The brazing material shall conform to IS 2927 or ISO 17672 or the brazing alloys listed in Annex D.’

[Page 9, **B-2.1**, (see also Amendment No. 2)] — Substitute ‘IS 1608 (Part 1)/ISO 6892-1’ for ‘IS 1608 (Part 1) : 2018/ISO 6892-1 : 2016’.

[Page 9, **B-3.1**, (see also Amendment No. 2)] — Substitute ‘IS 2328/ISO 8492’ for ‘IS 2328 : 2018/ISO 8492 : 2013’.

[Page 9, **B-4.1**, (see also Amendment No. 2)] — Substitute ‘IS 2335/ ISO 8493’ for ‘IS 2335 : 2005/ISO 8493 : 1998’.

[Page 9, **B-6.1**, (see also Amendment No. 2)] — Substitute ‘IS 4748/ ISO 643’ for ‘IS 4748 : 2009/ISO 643 : 2003’.

[Page 9, **C-1.2**, (see also Amendment No. 2)] — Substitute ‘IS 1608 (Part 1)/ISO 6892-1’ for ‘IS 1608 (Part 1) : 2018/ISO 6892-1 : 2016’.

(Page 9, Annex A) — Substitute the following for the existing:

‘ANNEX A
(Clause 2)

LIST OF REFERRED STANDARDS

<i>IS/ISO No.</i>	<i>Title</i>
IS 277 : 2018	Galvanized steel strips and sheets (plain and corrugated) — Specification <i>(seventh revision)</i>
IS 440 : 1964	Methods of chemical analysis of copper <i>(revised)</i>
IS 737 : 2008	Wrought aluminium and aluminium alloy sheet and strip for general engineering purposes — Specification <i>(fourth revision)</i>
IS 1391 (Part 1) : 2017	Room air conditioners — Specification: Part 1 Unitary air conditioners <i>(third revision)</i>
IS 1391 (Part 2) : 2018	Room air conditioners — Specification: Part 2 Split air conditioners <i>(third revision)</i>
ISO 1554 : 1976	Wrought and cast copper alloys — Determination of copper content — Electrolytic method
IS 1608 (Part 1) : 2022/ISO 6892-1 : 2019	Metallic materials — Tensile testing: Part 1 Method of test at room temperature <i>(fifth revision)</i>

Price Group 2

Amendment No. 3 to IS 11329 : 2018

IS 2328 : 2018/ISO 8492 : 2013	Metallic materials — Tube — Flattening test (<i>third revision</i>)
IS 2335 : 2005/ISO 8493 : 1998	Metallic materials — Tube — Drift expanding test (<i>second revision</i>)
IS 2927 : 1975	Specification for brazing alloys (<i>first revision</i>)
IS 4748 : 2021/ISO 643 : 2019	Steel — Micrographic determination of the apparent grain size (<i>third revision</i>)
IS 9844 : 1981	Methods of testing corrosion resistance of electroplated and anodized aluminium coatings by neutral salt sprays
IS 9902 : 2004	Recommended practices for leak testing (<i>first revision</i>)
IS 10773 : 1995	Wrought copper tubes for refrigeration and air-conditioning purposes — Specification (<i>first revision</i>)
ISO 17672 : 2024	Brazing — Filler metals'

[Page 9, Annex A, (see also Amendment No. 2)] — Insert the following new Annex:

‘ANNEX D
(Clause 6.2.1.5)

CHEMICAL COMPOSITION FOR BRAZING ALLOYS

D-1 CHEMICAL COMPOSITION FOR Cu-Ag-P AND OTHER ALLOYS

The chemical composition for Cu-Ag-P alloys are listed in Table 3. The chemical composition for other types of alloys are listed in Table 4. For testing of alloys as listed in Table 3 and Table 4, ISO 17672 shall be followed.

Table 3 Cu-Ag-P Alloy Composition
(Clause D-1)

SI No.	Alloy Composition Number	Cu	Ag	P	Other Elements Total
(1)	(2)	(3)	(4)	(5)	(6)
i)	3-1	Remainder	-	7.0-8.25	≤ 0.15
ii)	3-2	Remainder	0.8-1.2	6.8-7.2	≤ 0.15
iii)	3-3	Remainder	1.8-2.2	6.0-7.3	≤ 0.15
iv)	3-4	Remainder	1.8-2.2	6.8-7.7	≤ 0.15
v)	3-5	Remainder	4.8-5.5	5.8-7.0	≤ 0.15
vi)	3-6	Remainder	5.5-6.5	5.9-6.2	≤ 0.15
vii)	3-7	Remainder	14.5-15.5	4.5-5.2	≤ 0.15

Table 4 Other Types of Alloy Composition
(Clause D-1)

Sl No.	Alloy Composition Number	Cu	Ag	P	Cd	Zn	Sn	Fe	Mn	Ni	Pb	Al	Si	Other Elements Total
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)	(14)	(15)
i)	4-1	Remainder	-	6.0-7.0	-	-	6.0-7.0	-	-	-	-	-	0.01-0.40	≤ 0.15
ii)	4-2	25-27	34-36	-	17-19	19-23	-	-	-	-	-	-	-	≤ 0.15
iii)	4-3	31-33	34-36	-	-	31-35	-	-	-	-	-	-	0.05	≤ 0.15
iv)	4-4	Remainder	4.7-6.3	6.8-7.7	-	-	3.5-4.5	-	-	-	-	-	-	≤ 0.15
v)	4-5	29-31	39-41	-	-	26-30	1.5-2.5	-	-	-	-	-	-	≤ 0.15'

(MED 03)

Publication Unit, BIS, New Delhi, India