

**AMENDMENT NO. 3 FEBRUARY 2013
TO
IS 177 : 1989 COTTON DRILLS — SPECIFICATION**

(Page 1, clause 2) — Substitute the following for the existing:

‘2 REFERENCES

The standards listed in Annex A contain provisions which through reference in this text constitute provision of this standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated in Annex A.’

(Page 1, clause 3.2.1, sentence 1) — Insert the following at the end:

‘The dyed fabric shall be free from banned dyes, banned chemicals and heavy metals’.

(Page 1, clause 3.2.2) — Insert the following at the end:

‘Chlorine bleach shall not be used for the purpose’

[Page 3, Table 2 (see also Amendment No. 2)] — Insert the following table for the existing:

Table 2 Chemical Requirements of Cotton Drills
(Clause 4.2)

Sl No.	Characteristics	Requirement	Method of Test, Ref to IS
(1)	(2)	(3)	(4)
i)	Minimum colour fastness rating to:		
	a) Light (see Note):	4	IS 686 or IS 2454

Amend No. 3 to IS 177 : 1989

SI No.	Characteristics	Requirement		Method of Test, Ref to IS
(1)	(2)	(3)		(4)
	b) Washing: Test 5:			IS/ISO 105-C10
	1) Change in colour	4		
	2) Staining of adjacent fabrics	4		
	c) Bleaching	4		IS 762
	d) Perspiration, acidic and alkaline:			IS 971
	1) Change in colour	4		
	2) Staining of adjacent fabrics	4		
ii)	Scouring loss, percent, <i>Max</i> :			IS 1383 (Mild method)
	a) Grey	7.5		
	b) scoured, bleached or dyed	2.0		
iii)	pH value:	6.0 - 8.5		IS 1390 (Cold method)
iv)	Shrinkage or elongation, present, <i>Max</i> :	Warpway	Weftway	IS 2977
	a) Grey (for variety 2 only)	8.0	8.0	
	b) Bleached or dyed	4.0	4.0	
	c) Bleached/dyed and preshrunk	3.0	3.0	
	d) Mercerized and preshrunk (for variety 4 only)	1.0	1.0	
v)	Water solubles percent, <i>Max</i> (for bleached cloth only):			IS 3456
	a) Unmercerized	1.0		
	b) Mercerized	1.4		
vi)	Ash content, percent, <i>Max</i> (for bleached, mercerized and preshrunk cloth only)	0.5		IS 199
vii)	Barium activity number, <i>Min</i> (for mercerized cloth only)	120		IS 1689

NOTE — In case of dispute, colour fastness to light shall be determined by the method prescribed in IS 686.

(Page 4, Annex A) — Delete ‘IS 3417 : 1979 colour fastness of textile materials to washing: Test 5 (*first revision*).’

Amend No. 3 to IS 177 : 1989

(Page 4, *Annex A*) — Substitute the following or the end of Annex A:

‘IS/ISO 105 C-10:2006 Textiles — Tests for colour fastness Part C10 Colour fastness to washing with soap or soda and soda’