

AMENDMENT NO. 1 OCTOBER 2026
TO
IS 2112 : 2025 SILVER AND SILVER ALLOYS, JEWELLERY/ARTEFACTS —
FINENESS AND MARKING — SPECIFICATION
(Fourth Revision)

(Page 1, clause 1.2) — Substitute the following for the existing:

‘This standard also specifies the requirement for marking of fineness and other details to be marked on tested silver bullion, coin and jewellery/artefact.

NOTE — Artefacts cover medallions, utensils and any article of silver.’

(Page 1, clause 2) — Insert the following at the end:

‘IS 19563 : 2026/ISO 18214 : 2024 Jewellery and precious metals determination of high purity gold silver platinum and palladium difference method using SPARK-OES.’

(Page 1, clause 3.3) — Substitute the following for the existing:

‘**3.3 Silver Coin** — A Silver coin, under the scope of this standard, is a flat sheet of 999.9, 999.5 and 999.0 grade of silver of any shape and size having no value of legal tender and manufactured only by mints/refinery. Note: Anything of similar shape and purity less than or equal to 999.0, not manufactured by mints/refinery shall be treated as an artefact.’

(Page 1, clause 5) — Substitute the following for the existing:

‘5 GRADES

Fine silver and silver alloys shall be classified in accordance with the following grades depending upon their fineness:

Sl No.	Grade	Fineness (Parts per Thousand)	Remarks
(1)	(2)	(3)	(4)
i)	9999	999.9	} Fine silver for bullion and coins
	9995	999.5	
	999	999.0	
ii)	999	999.0	Fine silver for jewellery/artefacts
ii)	990	990.0	} Silver alloys for jewellery/artefacts
	970	970.0	
	958	958.0	
	925	925.0	
	900	900.0	
	835	835.0	
	800	800.0	

NOTE — All the above grades of silver and silver alloys shall be free from cadmium and lead.

Amendment No. 1 to IS 2112 : 2025

(Page 2, clause 6.3, line 2) — Substitute the following for the existing:

‘grades 900, 925, 958, 970 and 990, the solder of purity’

(Page 2, clause 6.4) — Substitute the following for the existing:

‘6.4 Sampling

6.4.1 Unless otherwise specified for the jewellery/artefacts of the same design and quality, the sample shall be taken from 10 percent of the semifinished/finished jewellery/artefacts. Any other sampling plan may also be followed subject to the agreement between the contracting parties or as specified by the inspection agency as the case may be. The sampling plan mentioned in IS 15820 may also be referred.

6.4.2 The sampling of bullion and coins shall be done as per the following:

6.4.2.1 In case of testing of fine silver by gravimetric method as per IS 2113, sampling shall be done as per IS 2113.

6.4.2.2 In case of testing of fine silver by IS 16900, sampling shall be done as per IS 16900.

6.4.2.3 In case of testing of fine silver by IS 19563, the following sampling plan shall be followed:

6.4.2.3.1 *Dip sampling*

The dip sample should be taken at the final stage of production, that is just before casting. The refinery may use its established dip-sampling procedure, provided that the sample obtained is representative of the melt and is capable of yielding a test specimen of minimum dimensions 25 mm × 25 mm × 5 mm.

6.4.2.3.2 *Sampling of bullion*

A representative sample shall be obtained from the finished bullion bar by cutting across the cross-section, preferably from two different locations, into pieces of approximately 25 mm × 25 mm × 5 mm each.

6.4.2.3.3 *Sampling of coin*

The coin selected for testing shall preferably have a minimum thickness of 2 mm and a minimum diameter of 25 mm to facilitate accurate determination of fineness. Where the dimensions are smaller, suitable sample preparation techniques may be adopted to ensure reliable test results.’

(Page 2, clause 6.5) — Substitute the following for the existing:

‘6.5 Assaying

6.5.1 The sample taken as prescribed in 6.4 shall be assayed as specified in Table 1. The actual weight of samples, shall however, be as prescribed in respective test methods.

Table 1 Applicability of Assaying Methods

(Clause 6.5.1)

Sl No.	Fineness (ppt)	Applicable Test Method
(1)	(2)	(3)
i)	999.9	IS 16900 or IS 19563
ii)	999.5	IS 2113 (Gravimetric method only) or IS 16900 or IS 19563
iii)	999	IS 2113 (Gravimetric method only) or IS 16900 or IS 19563
iv)	≤ 990	IS 2113

Amendment No. 1 to IS 2112 : 2025

6.5.2 Detection of cadmium and lead in silver and silver alloys shall be carried out by X-ray fluorescence (XRF) method.

(Page 2, clause 6.6) — Insert the following at the end:

‘6.7 Re-testing (Testing of Hallmarked Jewellery/Artefacts)

In case of testing of the hallmarked jewellery/artefact, a negative tolerance of maximum 10 PPT is permitted.’

(MTD 10)

Publication, BIS, New Delhi