

AMENDMENT NO. 1 AUGUST 2026
TO
IS 232 : 2020 GLOSSARY OF TEXTILE TERMS — NATURAL FIBRES
(Third Revision)

(Page 1, clause 4) — Insert the following definitions in alphabetical manner:

‘Ageing/Aging — The change in physical, chemical or mechanical properties of a material over time due to exposure to environmental factors such as heat, light, oxygen, moisture or chemicals.

Artificial/Accelerated Ageing — The process of simulating long-term environmental effects in a short time using controlled stress factors like UV radiation, heat, humidity, ozone or chemicals.

Biodegradability — Ability of a material to be broken down naturally in terms of weight, strength or both by microorganisms such as bacteria and fungi into basic natural substances like water, carbon dioxide, biomass and mineral salts.

Coagulation — A process by which an adhesive or chemical formulation transforms from a liquid state to a gel or semi-solid, forming a uniform layer or ‘clot’ on the surface of a natural fibre to ensure adhesion or coating.

Composites — A material composed of two or more distinct constituent materials, differing in physical or chemical properties, which remain separate and identifiable within the final structure and when combined, produce a material with characteristics superior to those of the individual components.

Compostability — Ability of a material to undergo biodegradation under controlled composting conditions (temperature, moisture, aeration, microbial activity) resulting in non-toxic, humus-like compost within a specified period.

Disintegration — The physical fragmentation or structural breakdown of a material during soil burial into smaller pieces without necessarily complete mineralization.

Flexing — Repeated bending, folding or oscillating deformation applied to a material to evaluate its resistance to fatigue or cracking.

Flexural Stress — Stress developed in the specimen due to bending during the flexing test.

Flexural Modulus — A measure of the material’s stiffness during bending.

Flexing Cycle — One complete movement of the test apparatus that bends the specimen forward and backward.

Flex Crack Index (FCI) — A numerical index representing the degree of cracking after specified cycles.

Green Composites — Materials made from renewable, natural sources like plant fibres (flax, hemp, wood, banana) or animal fibres, combined with natural/bio-based polymers (resins) for a matrix.

Kasturi Cotton — A premium brand of cotton, promoted by the Ministry of Textiles, Government of India, wherein each bale is certified on the basis of compliance with benchmark quality parameters, namely staple length, uniformity index, micronaire, tenacity, colour and trash content percentage. *Kasturi* cotton is certified across a wide staple length range from 28 mm+ to 35 mm+ and is provided with confirmation of origin, verifiable and traceable through blockchain technology across the entire value chain. By conforming to quantifiable standards of superior quality, *Kasturi* cotton enhances the softness, strength and durability of fabrics manufactured from it.

Price Group 1

Amendment No. 1 to IS 232 : 2020

Matrix — A continuous phase in a composite material that surrounds, binds and protects the reinforcement and transfers load to it.

Natural Ageing — Exposure of materials to real environmental conditions (sunlight, temperature fluctuations, humidity, air pollutants) over an extended period.

Organic Cotton — A cotton grown and processed according to organic farming standards, without the use of synthetic pesticides, artificial fertilizers, genetically modified (GM) seeds or harmful chemicals and is produced using methods that maintain soil health, conserve biodiversity and promote ecological balance.

Puncture Resistance — Maximum force or energy a material can withstand before being penetrated by a standard probe applied at a defined rate and orientation.

Puncture Force — Maximum force (N) required to penetrate the specimen using a specified probe.

Puncture Strength Index — A normalized performance parameter obtained by dividing the puncture resistance (peak puncture force) of a material by its thickness, providing a comparative measure of puncture performance independent of material thickness.

Reinforcement — A discontinuous, stronger and stiffer phase in a composite that provides mechanical strength, stiffness and load-bearing capability.

Water Vapour Permeability — Ability of a material to allow water vapour to diffuse through it under specified environmental conditions, such as temperature, relative humidity and pressure and is usually expressed as the rate of water vapour transfer per unit area over a given time.

Water Vapour Transmission Rate (WVTR) — Rate at which water vapour passes through a material per unit area over a specified period under controlled environmental conditions of temperature and relative humidity.'