

AMENDMENT NO. 1 JANUARY 2024

TO

**IS 233 (PART 4) : 2020 TEXTILES — METHODS FOR DETERMINATION
OF LENGTH PARAMETERS OF COTTON FIBRES**

**PART 4 ESTIMATION OF LENGTH, UNIFORMITY RATIO AND UNIFORMITY
INDEX BY THE OPTICAL SCANNING METHOD**

(*Second Revision*)

[Page 2, Table 1] — Substitute the following for the existing:

**Table 1 Quality Characteristics of ICAR-CIRCOT Calibration Cottons for High Volume Instrument
(HVI Mode)**

(Clause 5.2.1)

Sl No.	Code	UHML	Uniformity Index (UI)	Micronaire Value	Tenacity @ 3.2 mm Gauge Length	Elongation
		mm	Percent	µg/inch	g/tex	Percent
(1)	(2)	(3)	(4)	(5)	(6)	(7)
i)	S	Below 25	77 to 80	5.0 to 5.8	19.5 to 25	5.0 to 5.5
ii)	L	29 to 31	80 to 84	2.7 to 4.5	30.0 to 35.0	5.0 to 6.5
iii)	ELS-S	27.5 to 31	80 to 84	2.5 to 4.5	29 to 32	5.0 to 6.5
iv)	ELS-L	31.5 to 34.0	81 to 86	2.5 to 4.5	32.0 to 42.0	5.9 to 7.0
v)	Tolerance	± 0.5	± 1.0	± 0.1	± 1.5	—

NOTES

1 The label of each calibration cotton shows the exact test values of each parameter and lot number. The values of the different parameters of each calibration cotton differ based on the lot number.

2 The tolerance shall be applicable on the exact test values of the lot as indicated on the label of calibration cotton.

[Page 2, Table 2] — Substitute the following for the existing:

**Table 2 Quality Characteristics of ICAR-CIRCOT Calibration Cottons for High Volume Instrument
(ICC Mode)**

(Clause 5.2.1)

Sl No.	Code	2.5 Percent Span Length	Uniformity Ratio (UR)	Micronaire Value	Tenacity @ 3.2 mm Gauge Length	Elongation
		mm	Percent	µg/inch	g/tex	Percent
(1)	(2)	(3)	(4)	(5)	(6)	(7)
i)	S	Below 25	43 to 49	5.0 to 5.8	16 to 23	5.0 to 5.5
ii)	L	29 to 31	43 to 48	2.7 to 4.5	23 to 28	5.0 to 5.8
iii)	ELS-S	27.5 to 31	43 to 48	2.7 to 3.5	21 to 28	5.5 to 6.0
iv)	ELS-L	31.5 to 34.0	43 to 48	2.5 to 3.8	28 to 35	5.9 to 7.0
v)	Tolerance	± 0.5	± 1.0	± 0.1	± 1.5	—

NOTES

1 The label of each calibration cotton shows the exact test values of each parameter and lot number. The values of the different parameters of each calibration cotton differ based on the lot number.

2 The tolerance shall be applicable on the exact test values of the lot as indicated on the label of calibration cotton.