

AMENDMENT NO. 2 APRIL 2025
TO
IS 280 : 2006 MILD STEEL WIRE FOR GENERAL ENGINEERING PURPOSES
(Fourth Revision)

(Page 1, clause 2) — Substitute the following for the existing:

<i>‘IS No.</i>	<i>Title</i>
IS 228 (in various parts)	Methods for chemical analysis of steels
IS 1387 : 1993	General requirements for the supply of metallurgical materials (<i>second revision</i>)
IS 1608 (Part 1) : 2022/ ISO 6892-1 : 2019	Metallic materials — Tensile testing: Part 1 Method of test at room temperature (<i>fifth revision</i>)
IS 1755 : 2018/ISO 7802 : 2013	Metallic materials — Wire — Wrapping test (<i>second revision</i>)
IS 1956 (Part 3) : 2019	Glossary of terms relating to iron and steel: Part 3 Long products (including bars, rods, sections and wires) (<i>second revision</i>)
IS 4905 : 2015/ ISO 24153 : 2009	Random sampling and randomization procedures (<i>first revision</i>)
IS 6745 : 1972	Methods for determination of mass of zinc coating on zinc coated iron and steel articles
IS 7887 : 1992	Mild steel wire rod for general engineering purposes — Specification (<i>first revision</i>)’

(Page 1, clause 3, line 2) — Substitute ‘IS 1956 (Part 3)’ for ‘IS 1956 (Part 5)’.

(Page 1, clause 9.1, line 2) — Substitute ‘IS 1608 (Part 1)’ for ‘IS 1608’.

(Page 2, clause 10) — Substitute the following for the existing:

‘10 FINISH

The wire shall have one of the following finishes as specified by the purchaser:

- a) Annealed;
- b) Annealed, cleaned and limed;
- c) Bright drawn;
- d) Dull grey (dry drawn);
- e) Galvanized;
- f) Coppered;
- g) Tinned;
- h) Zn-Al coated;
- j) Coated and drawn (coating maybe of tin, copper, zinc or Zn-Al); and

Price Group 2

Amendment No. 2 to IS 280 : 2006

k) Any other metallic coating.’

(Page 2, clause 11.1) — Substitute the following for the existing:

‘11.1 When determined in accordance with IS 6745, the minimum mass of galvanized (Zn) coating (both hot dip galvanized or electro-galvanized) and coating of Zn-Al alloy on steel wire shall conform to the requirements for any one of the types of coatings given in Table 3. For sizes other than mentioned in Table 3, the minimum mass of galvanized coating and coating of Zn-Al alloy of steel wire shall conform to the requirements as agreed to between the manufacturer and the purchaser.’

(Page 2, clause 11.1) — Insert the following at the end:

‘Table 3 Coating Mass Per Unit Area

(Clause 11.1)

SI No.	Diameter, d	Class				
		A	AB	B	C	D
	mm	g/m^2	g/m^2	g/m^2	g/m^2	g/m^2
(1)	(2)	(3)	(4)	(5)	(6)	(7)
i)	$0.15 \leq d < 0.20$	—	—	15	—	10
ii)	$0.20 \leq d < 0.25$	30	20	20	20	15
iii)	$0.25 \leq d < 0.32$	45	30	30	25	15
iv)	$0.32 \leq d < 0.40$	60	30	30	25	15
v)	$0.40 \leq d < 0.50$	85	55	40	30	15
vi)	$0.50 \leq d < 0.60$	100	70	50	35	20
vii)	$0.60 \leq d < 0.70$	115	80	60	40	20
viii)	$0.70 \leq d < 0.80$	130	90	60	45	20
ix)	$0.80 \leq d < 0.90$	145	100	70	50	20
x)	$0.90 \leq d < 1.00$	155	110	70	55	25
xi)	$1.00 \leq d < 1.20$	165	115	80	60	25
xii)	$1.20 \leq d < 1.40$	180	125	90	65	25
xiii)	$1.40 \leq d < 1.65$	195	135	100	70	30
xiv)	$1.65 \leq d < 1.85$	205	145	100	75	30
xv)	$1.85 \leq d < 2.15$	215	155	115	80	40
xvi)	$2.15 \leq d < 2.50$	230	170	125	85	45
xvii)	$2.50 \leq d < 2.80$	245	185	125	95	45
xviii)	$2.80 \leq d < 3.20$	255	195	135	100	50
xix)	$3.20 \leq d < 3.80$	265	210	135	105	60
xx)	$3.80 \leq d < 4.40$	275	220	135	110	60
xxi)	$4.40 \leq d < 5.20$	280	220	150	110	70
xxii)	$5.20 \leq d < 8.20$	290			110	80
xxiii)	$8.20 \leq d \leq 10.00$	300			110	80

Amendment No. 2 to IS 280 : 2006

(Page 2, clause **11.2**) — Substitute the following for the existing:

‘11.2 The coating weight and test method for finishes other than galvanized (Zn) and Zn-Al alloy coated shall be subject to agreement between the purchaser and the manufacturer.’

(Page 2, clause **15.2**) — Substitute the following for the existing:

‘15.2 BIS Certification Marking

The product(s) conforming to the requirements of this standard may be certified as per the conformity assessment schemes under the provisions of the *Bureau of Indian Standards Act, 2016* and the Rules and Regulations framed thereunder, and the product may be marked with the Standard Mark.’

(Page 2, clause **15.2.1**) — Delete.

(Page 3, clause **A-2.1**, line 2) — Substitute ‘Table 4’ for ‘Table 3’.

(Page 3, Table 3, title) — Substitute ‘Table 4’ for ‘Table 3’.

(Page 3, clause **A-3.1**, line 1) — Substitute ‘Table 4’ for ‘Table 3’.

(Page 3, clause **A-3.1**, line 8) — Substitute ‘Table 4’ for ‘Table 3’.

(Page 3, clause **A-3.2**, para 2, line 3) — Substitute ‘Table 4’ for ‘Table 3’.

(MTD 04)

Publication, BIS, New Delhi