

**AMENDMENT NO. 2 MARCH 2026**  
**TO**  
**IS 303 : 2024 PLYWOOD FOR GENERAL PURPOSES — SPECIFICATION**  
**( Fourth Revision )**

(Foreword, fourth and fifth paragraph) — ‘Delete’.

[Page 1, clause **4.3** (see also Amendment No.1)] — Substitute the following for the existing:

‘**4.3** In terms of bending class, each grade of plywood shall be further classified in bending classes as follows:

- a) Bending Class 10;
- b) Bending Class 20;
- c) Bending Class 30;
- d) Bending Class 40; and
- e) Bending Class 50.’

(Page 1, clause **6.1**, line 2) — Substitute ‘manufacture’ for ‘manufacturer’.

(Page 1, clause **6.1**, line 4) — Substitute ‘such as’ for ‘includes’.

(Page 1, clause **6.2.1**, line 2 and line 3) — Delete ‘(aminoresins)’.

[Page 4, clause **8.2**, last paragraph (see also Amendment No.1)] — ‘Delete’.

[Page 5, Table 4, col (3), heading (see also Amendment No.1)] — Substitute ‘Bending Class’ for ‘Bending Class (F)’.

[Page 5, clause **11.5**, line 3, (see also Amendment No. 1)] — Substitute ‘90 percent’ for ‘10 percent’.

[Page 6, clause **11.6(b)**] — Substitute the following with existing:

‘b) Formaldehyde Class  $E_2$   $\leq$  30 mg/100 g of oven-dry sample’

(Page 6, clause **12**) — ‘Delete’.

[Page 6, clause **13.1(d)** (see also Amendment No.1)] — Insert the following at the end:

‘NOTE — The bending class shall be expressed with respect to minimum average value floored to 10s of  $MoR$  or  $MoE/100$ . For example, for average value of  $MoR$  (along the grain direction of the top veneer) is 28.3 N/mm<sup>2</sup>, average value of  $MoR$  (across the grain direction of the top veneer) is 34.2 N/mm<sup>2</sup>, average value of  $MoE$  (along the grain direction of the top veneer) is 4 100 N/mm<sup>2</sup> and average value of (across the grain direction of the top veneer) is 5 200 N/mm<sup>2</sup>, the bending class the plywood shall be Bending Class 20.’

Calculation;

$MoR \parallel$  = Modulus of rupture along the grain (N/mm<sup>2</sup>)

$MoR \perp$  = Modulus of rupture across the grain (N/mm<sup>2</sup>)

$MoE \parallel$  = Modulus of elasticity along the grain (N/mm<sup>2</sup>)

$MoE \perp$  = Modulus of elasticity across the grain (N/mm<sup>2</sup>)

Scaled  $MoE$  values:

$$MoE \parallel^* = MoE \parallel / 100$$

$$MoE \perp^* = MoE \perp / 100$$

$V_{\min}$  = Minimum value of variables

$$V_{\min} = \text{Min} (MoR \parallel, MoR \perp, MoE \parallel^*, MoE \perp^*)$$

**Price Group 1**

## Amendment No. 1 to IS 303 : 2024

The following expression defines the floored value of the Bending Class (BC) based on the minimum value  $V_{\min}$ :

$$floor_{BC} = 10 \times [V_{\min}/10]$$

where

$floor_{BC}$  = represents the floored value of BC;

$V_{\min}$  = minimum value of the variable under consideration; and

$[ ]$  = the floor function, which rounds down to the nearest integer.

The expression divides  $V_{\min}/10$ , applies the floor function, and then multiplies the result by 10.

Example calculation for determining Bending class is as given below:

$$MoR // = 28.3 \text{ N/mm}^2$$

$$MoR \perp = 34.2 \text{ N/mm}^2$$

$$MoE // = 4\,100 \text{ N/mm}^2 \rightarrow MoE //^* = 41$$

$$MoE \perp = 5\,200 \text{ N/mm}^2 \rightarrow MoE \perp^* = 52$$

Then

$$V_{\min} = \text{Min} (28.3, 34.2, 41, 52) = 28.3$$

$$BC = 10 \times [28.3/10] = 10 \times 2 = 20$$

[Page 6, clause **13.1(j)** (see also Amendment No.1)] — ‘Delete’.

(Page 7, clause **14**, last sentence) — Delete

‘For ECO-Mark the material used for packaging of the plywood shall be recyclable, reusable or biodegradable’.