

AMENDMENT NO. 1 MARCH 1992
TO
IS 620 : 1985 SPECIFICATION FOR WOODEN TOOL
HANDLES GENERAL REQUIREMENTS

(Fourth Revision)

(Page 5, clause 4.2, line 2) — Delete the words 'and not less than 8 percent'.

(Page 5, clause 5.1, Note) — Substitute the following new clause for the existing Note:

'5.1.1 It is recommended that, immediately after manufacture, all tool handles be dipped momentarily in raw linseed oil at room temperature, as this treatment retards changes in moisture content.'

(Page 5, clause 6.2) — Substitute the following for the existing clause:

'6.2 Tolerances — Unless otherwise specified in the relevant Indian Standard for the various types of wooden tool handles, the following tolerances shall be permissible:

a) Where the head, socket, blade or tongue of the tool is to be fitted	+ 3 mm - 0
b) At other places	± 2 mm
c) On overall length of the tool handle	± 3 mm for handles up to 300 mm ± 5 mm for handles from 310 mm to 600 mm ± 10 mm for handles from 610 mm and above

(Page 7, Appendix A) — Insert the following matter:

'Leucaena leucocephala Su - babul 94 '

(Page 9, Appendix B) — Insert the following matter:

<i>'Acacia tortilis</i>	Israeli babool	87
<i>Adina obliogocephala</i>	Haldusopa	80
<i>Albizia lucida</i>	Taprie siris	83
<i>Eucalyptus tereticornis</i>	Mysore gum	77
<i>Robinia - psued - acacia</i>	Black locust	82 '

(Page 10, Appendix C) — Insert the following matter :

<i>'Acacia mearnsii</i>	Black wattle	67
<i>Aphanamixis polystachya</i>	Pitraj	74 '

(CED 9)

Reprography Unit, BIS, New Delhi, India