

AMENDMENT NO. 1 MARCH 2000
TO
IS 708 : 1987 SPECIFICATION FOR POTASSIUM
CHLORATE FOR EXPLOSIVE AND PYROTECHNIC
INDUSTRY
(Second Revision)

(Page 3, clause A-7.2) — Substitute the following for the existing clause:

'A-7.2 **Procedure** — Dry the material over sulphuric acid for 24 h. Weigh accurately about 0.3 g of sample and dissolve it in 50 ml of water. Transfer this to a 250 ml volumetric flask and quickly dilute to the mark. Take exactly 50 ml of this solution in a 250 ml conical flask. Add 50 ml of ferrous sulphate (or ferrous ammonium sulphate) solution and about 10 ml of dilute sulphuric acid, close the flask with a stopper to prevent access of air and boil for 15 minutes. Cool the contents of the flask, add 10 ml of manganous sulphate solution and titrate the excess of ferrous sulphate solution against standard potassium permanganate. Run a blank in the same manner with 50 ml of ferrous sulphate (or ferrous ammonium sulphate) solution and about 10 ml of dilute sulphuric acid. The difference between the volume of potassium permanganate consumed in the blank and the sample represents the potassium chlorate content.'

(Page 3, clause A-7.3) — Substitute the following for the existing formula:

$$\text{'Potassium chlorate,} \\ \text{percent by mass} = 2.043 \frac{(V_2 - V_1) \times 5N}{M}$$

(CHD 26)