

**AMENDMENT NO. 1 MARCH 2001
TO
IS 709 : 1974 SPECIFICATION FOR MEDIUM
STRENGTH AIRCRAFT PLYWOOD
(First Revision)**

(*Page 7, clause 4.6*) — Substitute the following for the existing:

‘4.6 Treatment of Boards — Boards shall be treated with either trichlorophenol dissolved in light organic solvent or sodium pentachlorophenate dissolved in water to a retention level of 8 kg/m³ or 6 kg/m³ respectively.’

(CED 20)

Reprography Unit, BIS, New Delhi, India