

AMENDMENT NO. 1 MARCH 2025
TO
IS 13745 : 2020 METHOD FOR DETERMINATION OF FORMALDEHYDE
CONTENT IN WOOD-BASED PANELS BY EXTRACTION METHOD CALLED
PERFORATOR METHOD
(First Revision)

(Page 3, clause 5.1, line 3) — Substitute ‘an either end’ for ‘a front side’.

(Page 3, clause 5.1, line 3) — Substitute ‘12’ for ‘18’.

(Page 3, clause 5.2, first sentence) — Insert the following at the end:

‘after cooling’.

(Page 3, clause 5.2, line 6) — Substitute ‘72 h’ for ‘24 h’.

(Page 3, clause 5.3, line 2) — Substitute ‘already installed or from site/market’ for ‘already installed’.

(Page 3, clause 5.3, last sentence) — Substitute the following for the existing:

‘Unless otherwise agreed/specified, the test pieces shall be conditioned to a constant mass at a temperature of $27\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$ and a relative humidity of 65 percent ± 5 percent. Constant mass is considered to have been reached when the results of two successive weighing carried out at intervals of not less than 24 h do not differ by more than 0.1 percent of the mass of the test pieces.’

(Page 3, clause 6.2, last sentence) — Substitute the following for the existing:

‘The moisture content (M) of the board, in percent, is calculated by the equation:’

(Page 3, clause 6.2, equation) — Substitute the following for the existing:

$$\text{‘Moisture content } (M), \text{ percent} = \frac{M_1 - M_0}{M_0} \times 100$$

where

M_1 = mass, in g, of sample before drying; and

M_0 = mass, in g, of sample after drying.’

(Page 4, clause 6.4) — Insert the following at the end:

‘NOTE – The quality of toluene is checked by this test. If the blank value of formaldehyde is higher than 1 mg/600 ml of toluene, the toluene shall be rejected.’

(Page 4, clause 8.1, line 2) — Substitute ‘6.3’ for ‘7.3’.

(Page 4, clause 8.2.2, last paragraph, second sentence) — Insert the following at the end:

‘A blank test with 20 ml distilled water is carried out in parallel.’

(Page 5, clause 8.2.3, line 6) — Substitute ‘15 μg ’ for ‘15 mg’.

Price Group 1

Amendment No. 1 to IS 13745 : 2020

(Page 5, clause 8.2.5, formula) — Substitute the following for the existing:

$$\text{'Perforator value'} = \frac{(A_s - A_b) \times f \times (100 + M) \times V}{m_H} \text{ mg/100 g}$$

where

- A_s = absorbance of the analysed extraction solution;
 A_b = absorbance of an analysis with distilled or demineralized water;
 f = slope of the standard curve, in milligrams per millilitre (mg/ml);
 M = moisture content of the wood-based panel as mass fraction, in percent;
 V = volume of the volumetric flask (2 000 ml); and
 m_H = mass of test pieces, in grams (g).'

[Page 5, Fig. 2, Sl No. (a) and (b)] — Substitute the following for the existing:

'Key

- X Absorbance ($A_s - A_b$)
Y Concentration of the diluted calibration solution 'c' 10^{-3} mg/ml'.

[Page 6, clause 9(b)] — Substitute 'location (factory, installed at sites, market, etc)' for 'location'.

[Page 6, clause 9(e)] — Substitute 'Density' for 'Bulk density'.