

AMENDMENT NO. 1 SEPTEMBER 2000
TO
IS 13798 : 1993 POLYURETHANE BASE: KNIFING
FILLER (TWO PACK) FOR EXTERIOR PAINTING OF
RAILWAY COACHES — SPECIFICATION

(*Title, cover page*) — Substitute the following for the existing title and wherever it appears subsequently:

KNIFING FILLER (TWO PACK) FOR POLYURETHANE
SYSTEM — SPECIFICATION'

(*Page 1, clause 4.1.1*) — Substitute the following for the existing:

'Knifing filler shall be either Type A, consisting of appropriate polyester resin or Type B, consisting of appropriate unsaturated polyol. In addition to these, knifing filler of both types shall also contain pigments, extenders, solvents and additives.'

(*Page 7, Table 1*) — Substitute the following for the existing table:

Amend No. 1 to IS 13798 : 1993

Table 1 Requirements for Knifing Filler (Two Pack)
for Polyurethane System

Sl No.	Characteristic	Requirement		Methods of Test	
		Type A	Type B	Annex	Ref to Part/ Section of IS 101
(1)	(2)	(3)	(4)	(5)	(6)
i)	Drying time:				
	a) Surface dry, <i>Max</i>	30 minutes	2 h	—	Part3/ Sec 1
	b) Hard dry, <i>Max</i>	6 h	18 h	—	—
	c) Hard dry, 70°C	2 h with 15 minutes flash off time	2 h with 15 minutes flash off time	—	
ii)	Consistency	Smooth and uniform and suitable for knife application	Smooth and uniform and suitable for knife application	—	Part 1/ sec 5
iii)	stopping properties	Shall show no sagging, cracking or shrinkage	Shall show no sagging, cracking or shrinkage	B	—
iv)	Rubbing properties	Shall dry rub with 180 grade paper and wet rub with 280 grade water proof paper without clogging of the paper and shall not show defects like roughness, scratches, cracks and pinhole after rubbing	Shall dry rub with 180 grade paper and wet rub with 280 grade water proof . paper without cloggttlg of the paper and shall not show defects like roughness, scratches, cracks and pinhole after rubbing	C	
v)	Hold out adhesion and compatibility in paint system	Finish with uniform gloss and colour with good adhesion and compatibility of the system	Finish with uniform gloss and colour with good adhesion and compatibility of the system	D	—
vi)	Pot life, <i>Min</i>	30 minutes	30 minutes	E	—
vii)	Keeping properties	Not less than six months	Not less than six months	—	Part 6/ Sec 2

(CHD31)

Reprography Unit, BIS, New Delhi, India