

**AMENDMENT NO. 1 JULY 1995
TO
IS 13851 : 1993 STORAGE AND REDRYING OF
COVERED ELECTRODES BEFORE USE —
RECOMMENDATIONS**

[Page 1, clause 3.1(d)] — Substitute the following for the existing matter:

‘The relative humidity (RH) condition of storage should be less than 50 percent.’

[Page 1, clause 3.1(e)] — Substitute the following for the existing matter:

‘The ideal storage temperature is 10-15°C above the ambient temperature.’

[Page 3, Table 1, Sl No. (i) (a), headed under ‘Temp (°C)’] — Substitute ‘100 ± 10¹’ for ‘135 ± 10¹’.

[Page 3, Table 1, Sl No. (iii), ‘Hardfacing (ii) Rutile, headed under ‘Temp (°C)’] — Substitute ‘135 ± 10’ for ‘360 ± 10’.

[Page 3, Table 1, Sl No. (vi), Aluminium, headed under ‘Temp (°C)’] — Substitute ‘110 ± 10’ for ‘180 ± 10’.

[Page 3, Table 1, Sl No. (vi), Aluminium, headed under ‘Time (min)’] — Substitute ‘120’ for ‘60’.

o