

AMENDMENT NO. 2 DECEMBER 2010
TO
IS 13851 : 1993 STORAGE AND REDRYING OF COVERED
ELECTRODES BEFORE USE — RECOMMENDATIONS

[Page 3, Table 1 (see also Amendment No.1)] — Substitute the following in place of the existing Table 1:

Table 1 Temperature — Time Cycle for Redrying of Electrodes
(Clause 4)

Sl No.	Electrode Type	Redrying Condition		Holding Condition Temp°C	Time Exposed
		Temp (°C)	Time (min)		
i)	General purpose mild steel cored:				
	a) Rutile (IS 814) coated	135 ±10	60	40-45	4 h
	b) Cellulose coated	Not recommended	—	Not recommended	Nil
	c) Basic coated (for extra low hydrogen, that is, less than 5 ml/100 g of weld)	300 ±10 or 360 ±10	120 60	130 ±10	9 h (2 h for Basic Coated only)
ii)	Stainless steel electrode	300 ±10	120	130 ±10	1 h
iii)	Hardfacing:				
	a) Basic	300 ±10	120	130 ±10	2 h
	b) Rutile	100 ±10	60	—	4 h
iv)	Cast iron	135 ±10	60	40-45	1 h
v)	Ni & Ni based	360 ±10	60	130 ±10	1 h
vi)	Non-ferrous:				
	a) Aluminium	180 ±10	60	—	Nil
	b) Copper	230 ±10	120	—	1 h

NOTE – Redrying to be done if the electrodes have remained exposed to humid condition (70 % RH and above) for a time as given above. Whenever the welding consumable manufacturers' recommendation is available for the redrying parameters, those recommendations shall supersede the above requirements.