

AMENDMENT NO. 1 JULY 2010
TO
IS 13885 : 2001 NON-MAGNETIC/CHAR IN SPONGE
IRON (DRI) — METHODS OF DETERMINATION
(First Revision)

(Page 1, clause 1) — Substitute the following for the existing:

‘This standard prescribes methods for determination of non-magnetics/char in truck load of sponge iron, in sponge iron stack and sponge iron packed in bags.’

(Page 1, clause 4.2.1, line 1) — Substitute ‘per’ for ‘par’.

(Page 1, clause 4.2.2, line 3) — Substitute ‘20 kg’ for ‘10 kg’.

(Page 1, clause 5.1, line 1) — Substitute ‘1 250 mm’ for ‘750 mm’.

(Page 2, clause 5.2.1) — Add the following at the end of the last sentence:

‘kept in contact with the materials. The typical intensity of the hand magnet should be 950 to 1 000 gauss.’

(Page 2, clause 5.3) — Add the following new clause after the 5.3:

‘6 DETERMINATION OF PERCENTAGE OF NON-MAGNETICS IN SPONGE IRON PACKED IN BAGS FROM TRUCK/WAGON/ STACK

6.1 Sampling — Sponge iron packed in bags, a sample shall be collected by random selection of bags. The minimum number of bags and increment shall be as per the table given below:

<i>Bag lot in Nos.</i>	<i>No. of bags sampled on random basis</i>	<i>No. of increments from each bag</i>	<i>Minimum mass of each increment</i>
Up to 200	20	2	1 kg
200-1 000	40	2	1 kg
1 000-5 000	60	2	1 kg
5 000-10 000	80	2	1 kg
10 000-25 000	100	2	1 kg
25 000-0 000	120	2	1 kg

Amend No. 1 to IS 13885 : 2001

6.2 Test Procedure

6.2.1 If the sample quantity is more than 20 kg, weight Sample reduction shall be made by coning and quartering method and if not, the entire quantity of sample shall be separated by hand magnet. The separation process will be repeated until all magnetics are collected by magnet kept in contact with the materials. The typical intensity of the hand magnet should be 950 to 1 000 gauss.

6.2.2 The sample so collected in sample container as per 6.2.1 shall be weighed and mass noted, say (Z).

6.2.3 The non-magnetics, thus left after magnetic separation shall be weighed and mass noted, say (Y).

6.3 Calculation

$$\text{Percentage of non-magnetics from sample} = \frac{Y}{Z} \times 100'$$

7 DETERMINATION OF PERCENTAGE OF NON-MAGNETICS IN SPONGE IRON FROM MOVING CONVEYORS

7.1 Sampling

25 kg sample of sponge iron lumps/fines shall be collected using standard shovels at the discharge end of the moving conveyors in two or three increments.

7.2 Test Procedure

Same as per **6.2**.

7.3 Calculation

Same as per **6.3**.

(MTD 30)