

AMENDMENT NO. 2 AUGUST 2023

TO

IS 13893 : 1994 POLYURETHANE SOLE, SEMIRIGID — SPECIFICATION

(Cover Page, Title) — Substitute the title with the following:

‘POLYURETHANE UNIT OUTSOLES — SPECIFICATION’

(Page 1, Title) — Substitute the following for the existing:

‘POLYURETHANE UNIT OUTSOLES — SPECIFICATION’

(Page 1, clause 1.1) — Substitute the following for the existing:

‘This standard prescribes the requirements and methods of sampling and test for polyurethane unit outsoles.’

(Page 1, clause 1.2) — Delete

(Page 1, clause 4.2) — Substitute the following for the existing:

‘The thickness of the soles shall be not less than 4 mm, at any portion of the sole, when measured in accordance with the method prescribed in IS (15298 Part 1) : 2015.’

(Page 1, clause 4.3) — Substitute the following for the existing:

‘Unless otherwise agreed to between the purchaser and the supplier, the polyurethane soles shall be tested for the requirements prescribed in 4.3.1 within three months from the date of receipt of the product.’

(Page 1, Table 1) — Substitute the following for the existing:

Physical Requirements for Polyurethane Unit Outsoles

(Clause 4.3.1)

Sl No.	Characteristic	Requirement	Method of Test, Ref to IS
(1)	(2)	(3)	(4)
i)	Relative density, <i>Max</i>	1.2	Annex C-1 of IS 10702
ii)	Hardness, degree Shore A, <i>Min</i>	40	IS 12240 (Part 2) : 1988
iii)	Abrasion resistance at applied force of 10 N (Volume loss), mm ³ , <i>Max</i>	350	IS 3400 (Part 3)
iv)	Flexing resistance Bennewart method, cut growth at the end of 30 000 cycles, mm, <i>Max</i> (Not applicable for rigid sole) ¹	6.0	Annex D of IS 15844 (Part 1)
v)	Hydrolysis resistance, cut growth after 150 000 flexes, mm, <i>Max</i> (Not applicable for rigid sole) ¹	6.0	IS 15298 (Part 1)
vi)	Tensile strength, MPa, <i>Min</i>	3.0	IS 3400 (Part 1)
vii)	Elongation at break, percent, <i>Min</i>	200	IS 3400 (Part 1)
viii)	Tear strength (average force), kN/m, <i>Min</i>	3.0	Method A of IS 3400 (Part 12)

NOTE — Rigid sole - The sole which do not bend at ball girth and which do not loose shape after application of manual force.

Price Group 2

Amendment No. 2 to IS 13893 : 1994

(Page 1, clause 4.3.2) — Delete

(Page 1, clause 5.1, second line) — Substitute the following for the existing:

‘The Outsoles may be packed as agreed to between the purchaser and the supplier. Each package may contain outsoles of same size only and may be marked with the name of the item, batch/code number, size, manufacturer’s name or its recognized trade-mark, if any.’

(Page 1, clause 5.2) — Substitute the following for the existing:

‘Each sole shall be marked legibly and indelibly with the following:

- a) Identification of the source of manufacturer or brand name; and
- b) Size of the footwear for which it is intended.’

(Page 1, clause 5.2.1.1) — Substitute the following for the existing:

‘The product(s) conforming to the requirements of this standard may be certified as per the conformity assessment schemes under the provisions of the *Bureau of Indian Standards Act*, 2016 and the Rules and Regulations framed thereunder, and the products may be marked with the Standard Mark.’

(Page 2, Annex A) — Substitute the following for the existing Annex A:

IS No.	Title	IS No.	Title
IS 1638 : 1969	Specification for sizes and fittings of footwear (<i>first revision</i>)	IS 4905 : 2015/ ISO 24153 : 2009	Random sampling and randomization procedures (<i>first revision</i>)
IS 2050 : 1991	Glossary of terms relating to footwear (<i>first revision</i>)	IS 10702 : 2023	Hawai chappal — Specification (<i>third revision</i>)
IS 3400	Methods of test for vulcanized rubber:	IS 12240 (Part 2) : 1988	Methods of test for polyvinyl chloride boots: Part 2 Determination of durometer hardness, Shore A
(Part 1) : 2021/ ISO 37 : 2017	Tensile stress-strain properties (<i>fourth revision</i>)	IS 15298 (Part 1) : 2015	Personal protective equipment: Part 1 Test methods for footwear (<i>second revision</i>)
(Part 3) : 2021/ ISO 4649 : 2016	Abrasion resistance using a rotating cylindrical drum device (<i>third revision</i>)	IS 15844 (Part 1) : 2023	Sports footwear: Part 1 General purpose (<i>first revision</i>)
(Part 12) : 2022/ ISO 34-1 : 2015	Tear strength — Trouser, angle and crescent test piece (<i>first revision</i>)		
(Part 16) : 1974	Measurement of cut growth of rubber by the use of the ross flexing machine		

(Page 2, Annex B) — Delete

(Page 3, clause C-1.1, line 2) — Delete “size”