

AMENDMENT NO. 2 JULY 2023
TO
IS 13917 : 2003 STRANDED WIRE ROPES FOR MINE HOISTING — TECHNICAL
DELIVERY REQUIREMENTS
(First Revision)

(Page 5, clause 5.1.4.2.2, second para) — Substitute the following for the existing:

<i>Sl No.</i>	<i>Rope Diameter (D)</i>	<i>Minimum Test Length (L)</i>
	<i>mm</i>	<i>mm</i>
(1)	(2)	(3)
i)	$d \leq 6$	300
ii)	$6 \leq d \leq 20$	600
iii)	$d > 20$	$30 \times d$

(Page 6, clause 5.1.4.2.5) — Substitute the following for the existing clause:

‘Not more than 80 percent of the minimum breaking force may be applied quickly, the remaining force shall be applied slowly, at a rate of application of force not more than 0.5 percent of minimum breaking force per second.’