

**AMENDMENT NO. 1 NOVEMBER 2008
TO
IS 13957 : 1994 METAL FACED PLYWOOD —
SPECIFICATION**

(Page 2, clause 6.1) — Substitute the following for the existing clause:

‘6.1 The dimensions of plywood boards shall be as follows:

2 400 mm × 1 200 mm	2 100 mm × 900 mm
2 100 mm × 1 200 mm	1 800 mm × 900 mm
1 800 mm × 1 200 mm	

NOTE – Any other dimensions as agreed to between the manufacturer and the purchaser may also be used.’

(Page 2, clause 6.3) — Substitute the following for the existing clause:

‘6.3 The following tolerances on the nominal sizes of finished boards shall be permissible:

<i>Dimension</i>	<i>Tolerance</i>
a) Length	+6 mm –0 mm
b) Width	+3 mm –0 mm
c) Thickness:	
1) Less than 6 mm	±10 percent
2) 6 mm and above	±5 percent
d) Squareness	0.2 percent or 2 mm per 1 000 mm
e) Straightness	0.2 percent or 2 mm per 1 000 mm

NOTE – Edge straightness and squareness shall be tested as per Annex B.’

(Page 3, Annex A) — Insert the following as a new annex after Annex A:

Amend No. 1 to IS 13957 : 1994

**‘ANNEX B
(Clause 6.3)**

METHOD OF TEST FOR EDGE STRAIGHTNESS AND SQUARENESS

B-1 PROCEDURE FOR EDGE STRAIGHTNESS

B-1.1 The straightness of the edges and ends of plywood shall be verified against a straight edge not less than the full length of the plywood. If the edge on the end of the plywood is convex, it shall be held against the straight edge in such a way as to give approximately equal gap at each end. The largest gap between the straight edge and the edge shall be measured to the nearest millimetre and recorded.

B-2 PROCEDURE FOR SQUARENESS

B-2.1 The squareness of plywood shall be checked with a set square of arms 500 mm long, by applying one arm of the square to the plywood. The maximum width of the gap shall be recorded.’

(CED 20)