

**AMENDMENT NO. 1 JANUARY 2005
TO
IS 13958 : 1994 BAMBOO MAT BOARD FOR
GENERAL PURPOSES — SPECIFICATION**

(*Page 2, clause 6.2*) — Substitute the following for the existing:

6.2 Dimensions of bamboo mat boards shall be as follows:

2 400 mm × 1 200 mm	1 800 mm × 1 200 mm
2 100 mm × 1200 mm	1 800 mm × 900 mm
2 100 mm × 900 mm	

NOTE — Any other dimension as agreed to between the manufacturer and the purchaser may also be used.

(*Page 2, clause 9.3.1, fourth line*) — Insert 'not less than' between 'of' and ' 0.7 N/mm^2 '.

(*Page 2, clause 9.3.2, last line*) — Insert 'not less than' between 'of' and ' 0.5 N/mm^2 '.

(*Page 2, clause 9.3.3, fifth and sixth line*) — Insert 'not less than' between 'of' and ' 0.5 N/mm^2 '.

(*Page 3, clause 9.4.1, fourth and fifth line*) — Insert 'not less than' between 'of' and ' 4.5 N/mm^2 '.

(*Page 3, clause 9.4.2, eighth line*) — Insert 'not less than' between 'of' and ' 3.0 N/mm^2 '.

(*Page 3, clause 9.4.3, last line*) — Insert 'not less than' between 'of' and ' 3.0 N/mm^2 '.

(*Page 3, clause 9.4.3*) — Add the following new clause after 9.4.3:

9.5 Test for Modulus of Rupture (MOR) and Modulus of Elasticity (MOE)

Three test specimens for MOR and MOE from each sample of dimension as specified in IS 2380 (Part 4), when tested for modulus of rupture and modulus of elasticity in accordance with the method prescribed in IS 2380 (Part 4), the average and minimum individual values shall be not less than the values given below:

Amend No. 1 to IS 13958 : 1994

	<i>Average</i>	<i>Minimum Individual</i>
MOE (N/mm ²)	3 000	2 700
MOR (N/mm ²)	2 700	27

(Page 3, Annex A) — Add the following at the appropriate place:

IS 2380 (Part 4) : 1977 Method of test for wood particle boards and boards
from other lignocellulosic material : Part 4 :
Determination of static bending strength (modulus of
rupture and modulus of elasticity in bending) (*first
revision*)

(CED 20)

Reprography Unit, BIS, New Delhi, India