

AMENDMENT NO. 4 APRIL 2012
TO
IS 1554 (PART 2) : 1988 SPECIFICATION FOR PVC INSULATED
(HEAVY DUTY) ELECTRIC CABLES

PART 2 FOR WORKING VOLTAGES FROM 3.3 kV UP TO
AND INCLUDING 11 kV

(Second Revision)

(Page 2, clause 2.2) — Renumber the existing Note as Note 1 and add Note 2 as given below:

‘NOTE 2 — When type tests have been successfully performed on a type of cable covered by this standard with a specific conductor cross-sectional area and rated voltage, type approval shall be accepted as valid for cables of the same type with other conductor cross-sectional areas and/or rated voltages provided the following three conditions are all satisfied:

- a) The same material, that is, insulation and semi-conducting screens, and manufacturing process are used.
- b) The conductor cross-sectional area is not larger than that of the tested cable.
- c) The rated voltage is not higher than that of the tested cable.

Approval shall be independent of the conductor material.’

(Page 4, clause 16.1.2) — substitute the following for the existing clause:

‘The armour wires/formed wires shall be applied as closely as possible with a coverage of not less than 90 percent. The coverage of armour shall be done as per Appendix C.’

[Page 10, Appendix B (see also Amendment No. 1)] — Add the following ‘Appendix C’ after ‘Appendix B’:

APPENDIX C

(Clause 16.1.2)

ARMOUR COVERAGE PERCENTAGE

$$\text{Percent coverage} = \frac{N \times d}{W} \times 100$$

where

N = number of parallel wires,
 d = diameter of wire/width of formed wires,

$W = \pi \times D \times \cos a$,

D = diameter under armour,

a = angle between armouring wire/formed wires and axis of cable,

$\tan a = \pi \times D/C$, and

C = lay length of armouring wires/formed wires.

