

AMENDMENT NO. 1 FEBRUARY 2003
TO
IS 1576 : 1992 SOLID PRESSBOARD FOR ELECTRICAL
PURPOSES — SPECIFICATION
(First Revision)

(Foreword, para 4, line 3) — Substitute 'Annex T' for 'Annex D'.

(Page 1, clause 5.2.1) — Substitute the following for the existing:

5.2.1 Tolerance on Normal Thickness — The thickness of the board at any point when measured in accordance with Annex B shall not differ from nominal thickness as per the following deviation permitted for Types A, B, C and D:

Thickness	Tolerance
≤ 1.6 mm	± 7.5 %
≥ 1.6 to 6.35 mm	± 5 %

[Page 3, clause 5.9(b)] — Insert the following after 5.9(b):

- c) Pressboards with nominal thickness other than that indicated in Table 1 shall be tested either for number of folds as stated for next higher thickness in Table 1 or it shall be bent round a mandrel as stated for next higher thickness in Table 1.

(Page 3, Table 1) — Substitute the following for the existing table:

Table 1 Flexibility
(Clauses 5.9 and G-3.2)

Type	Direction	Nominal Thickness, mm							
		0.80	1.60	0.80	1.60	2.00	3.20	4.75	6.35
		No. of Folds		Mandrel Diameter in Millimetres					
A	Machine	50	30	—	—	19.00	—	—	—
	Cross	50	30	—	—	13.00	—	—	—
B	Machine	50	30	—	—	19.00	25.00	38.00	—
	Cross	50	30	—	—	6.50	13.00	25.00	—
C	Machine	50	20	—	—	19.00	25.00	38.00	76.00
	Cross	50	20	—	—	13.00	19.00	25.00	51.00
D	Machine	—	—	6.50	19.00	25.00	38.00	76.00	125.00
	Cross	—	—	3.25	6.50	13.00	19.00	38.00	51.00

Amend No. 1 to IS 1576 : 1992

(Page 4, clause 5.11. informal table) — Substitute the following for the existing:

Type	Oil Absorption, Percent
B	15
C	20
D	15

(Page 4, clause 5.13. informal table) — Substitute 'micro ohms/cm' for 'mho/cm'.

(Page 7, Annex D, clause D-3.1, line 2) — Substitute 'sine-wave' for 'size-wave'.

(Page 7, Annex D, clause D-3.1, line 3) — Substitute ' $\sqrt{2 \pm 5}$ ' for ' 2 ± 5 '.

(Page 10, Annex F, clause F-7.1, line 2) — Substitute 'oven' for 'over'.

(Page 10, Annex F, clause F-7.3(b)) — Substitute ' h_2 ' for ' h_1 '.

(Page 14, Annex P, Title) — Substitute the following for the existing:

DETERMINATION OF FREEDOM FROM CONDUCTING PARTICLES

(Page 14, Annex P, clause P-3.2, line 2) —Substitute '2.0 kV/mm' for '4.0 kV/mm'.

(ET 02)