

AMENDMENT NO. 1 MARCH 2024
TO
IS 1582 : 2017 TEXTILES — SILK YARN AND FABRICS — DETERMINATION OF
DEGUMMING LOSS
(First Revision)

(Page 2, clause 9) — Substitute the following informal table for the existing:

<i>Sl No.</i>	<i>Type of Silk</i>	<i>Soap</i>	<i>Sodium Carbonate</i>
		(g/l)	(g/l)
(1)	(2)	(3)	(4)
i)	Mulberry and Muga	5	1
ii)	Eri/Endi	5	2
iii)	Tassar	7	3
iv)	Twisted/Thrown	5	1.5

NOTES

1 'Pure chemicals' shall mean chemicals that do not contain impurities which affect the test results.

2 Neutral soap as per IS /ISO 105 C 10 is suitable for this test.

3 pH of the degumming liquor may be maintained between 9.5 to 10.5.