

AMENDMENT NO. 2 APRIL 2012
TO
IS 1592 : 2003 ASBESTOS CEMENT PRESSURE PIPES AND JOINTS —
SPECIFICATION

(Fourth Revision)

[Page 2, clause 3.4.1.4(c)] — Add the following matter at the end:

‘The thickness shall be measured near the jointing surface of the pipe ends.’

[Page 2, clause 3.4.1.4(c), Note 3] — Add the following matter at the end:

‘For the purpose of measuring thickness at any point, measurement shall be made on pieces obtained from hydraulic bursting test and transverse crushing tests.’

(Page 8, Annex B) — Substitute ‘*Minimum Weight*’ for ‘*Weight*’ in the column heading 7 of the table.

(Page 8, Annex B) — Substitute the following for the existing matter at the end of the table:

TOLERANCES

The tolerance on dimensions of asbestos cement couplings shall be as follows:

Internal diameter (up to 600 mm dia)	+1.0 –0 mm
Internal diameter (700 mm and above)	+1.5 –0 mm
Outer diameter	+6 –0 mm
Length	+3 –0 mm
Thickness	+3 –0 mm

NOTES

- 1 Internal diameter : Average internal diameter of 3 places.
- 2 Thickness : Average thickness of 3 places (at other groove section).’

(CED 53)

Reprography Unit, BIS, New Delhi, India