

AMENDMENT NO. 1 NOVEMBER 2025
TO
IS 1628 : 1986 SPECIFICATION FOR AXLE OIL
(*Second Revision*)

(Page 5, Table 1) — Substitute the following for the existing:

TABLE 1 REQUIREMENTS FOR AXLE OIL

(Clause 3.2)

SI No.	CHARACTERISTICS	REQUIREMENTS FOR			METHOD OF TEST (Ref to [Part/Sec] in IS 1448) (6)
		Light Grade	Medium Grade	Heavy Grade	
(1)	(2)	(3)	(4)	(5)	(6)
i)	Acidity				
	a) Inorganic	Nil	Nil	Nil	Part 2 ¹⁾
	b) Organic (mg of KOH/g of the oil), <i>Max</i>	1.0	1.0	1.0	
ii)	Ash, percent by mass, <i>Max</i>	0.05	0.05	0.05	Part 4/Sec 1
iii)	Pour point, °C, <i>Max</i>	-3	-3	-3	Part 10/Sec 2
iv)	Copper-strip corrosion, for 3 h at 100 °C	Not worse than No. 1	Not worse than No. 1	Not worse than No. 1	Part 15
v)	Flash point closed (Pensky Martens), °C, <i>Min</i>	160	160	160	Part 21
vi)	Asphaltene content, percent by mass, <i>Max</i>	0.5	0.5	0.5	Part 22
vii)	Kinematic viscosity at 60 °C, in centistokes	64 to 71	76 to 86	90 to 103	Part 25
viii)	Water content, percent by mass, <i>Max</i>	0.5	0.5	0.5	Part 40
ix)	Saponification value (mg of KOH/g of the oil), <i>Max</i>	1.5	1.5	1.5	Part 55/Sec 1
x)	Viscosity index, <i>Min</i>	40	40	40	Part 56

¹⁾ Calculate the total acid number and strong acid number, expressed as milligrams of KOH per gram of the oil using this method, Inorganic acidity is equal to the strong acid number. Organic acidity is calculated by subtracting the strong acid number from the total acid number that is, Organic acidity = Total acid number — Strong acid number.