

AMENDMENT NO. 1 DECEMBER 2010
TO
IS 1654 : 1992 LEAD-ANTIMONY ALLOYS — SPECIFICATION

(*Third Revision*)

(Page 1, Table 1) — Substitute the following for the existing table:

Table 1 Chemical Composition of Lead-Antimony Alloys
(*Clauses 5.1 and 9*)

(Percentages are in maximum unless shown otherwise)									
Grade %	Antimony %	Arsenic %	Tin %	Copper %	Bismuth %	Iron %	Zinc %	Silver %	Lead %
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)
PbSb 1	0.8-1.2	—	—	0.05	0.03	0.003	0.001	0.02	Balance
PbSb 2	1.8-2.2	—	—	0.05	0.03	0.003	0.001	0.02	Balance
PbSb 5	4.5-5.5	—	—	0.05	0.03	0.003	0.001	0.04	Balance
PbSb 6	5.5-6.5	—	—	0.05	0.03	0.003	0.001	0.04	Balance
PbSb 8	7.5 - 8.5	—	—	0.05	0.03	0.003	0.001	0.04	Balance
PbSb 10	9.5 - 10.5	—	—	0.05	0.03	0.003	0.001	0.04	Balance
PbSb 5Sn	5.2 - 5.8	0.05 - 0.25	1.7 - 1.9	0.05	0.03	0.003	0.001	0.04	91-92

NOTES

1 The limits of arsenic and tin shall be subject to agreement between the supplier and the purchaser for all grades except grade PbSb 5Sn.

2 Other impurities do not preclude the possible presence of any other unnamed elements. However, analysis shall regularly be made only for the impurities listed in the table.

(MTD 9)