

AMENDMENT NO. 1 JUNE 2025
TO
IS 1660 : 2024 WROUGHT AND CAST ALUMINIUM UTENSILS —
SPECIFICATION
(Second Revision)

(Page 1, clause 1.1, Note) — Insert the following at the end:

‘4 Accessories like separators/containers, idli plate, steamer plate, dhokla plate, baking mold and similar accessories are not covered in this standard.’

(Page 1, clause 3.1.3) — Insert the following at the end:

‘3.1.4 The thickness of cast cookware shall be as given in Table 3.’

(Page 1, clause 4.1, Note) — Substitute the following for the existing:

‘NOTE — The material shall not contain more than 0.05 percent as metal of any toxic metals such as lead, cadmium and arsenic. Supplier certificate is acceptable.’

(Page 1, clause 4.1.1) — Substitute the following for the existing:

‘4.1.1 The lids, if provided shall comply to the requirements of IS 21 or IS 737 or IS 617 or stainless-steel conforming to IS 5522/grades of IS 5522 as per IS 6911 or IS 15997/grades of IS 15997 as per IS 6911. The minimum thickness of the stainless steel lid shall be 0.3 mm.’

(Page 2, clause 4.2) — Substitute the following for the existing:

‘4.2 The strips shall be manufactured from material conforming to IS 21 or IS 737. Stainless steel handles, rivets and fittings may also be used, which shall comply to IS 6603 or IS 6911 as applicable.’

(Page 2, clause 4.6) — Substitute the following for the existing:

‘4.6 The strips used for flame guards shall be manufactured from material conforming to IS 737 or IS 21 or IS 1285 or stainless steel as per IS 6911.’

(Page 2, clause 5.2) — Substitute the following for the existing:

‘5.2 In case of wrought aluminum utensils specified in 1.1(a), 1.2 and 1.3; the permissible reduction in the thickness of the finished utensils, taking into account the pressing or spinning process, shall not be more than 25 percent for pressing and 60 percent for spinning on the nominal sheet thickness specified as per Table 1, or 3.1.2.’

(Page 2, clause 5.3) — Substitute the following for the existing:

‘5.3 For thick bottom utensils, the wall thickness can go up to 60 percent reduction, however, the bottom thickness cannot exceed 5 percent of minimum sheet thickness.’

(Page 3, clause 8.7) — Substitute the following for the existing:

‘8.7 The cookware, if coated with powder coating or ceramic coating or high temperature resistant liquid coating or PTFE coating, fully or partially externally, shall conform to the thickness test, adhesion test as per IS 9730. The coating shall comply with IS 9806. The minimum thickness of the coating shall be 30 microns (powder coating) and 15 microns (ceramic coating, PTFE coating and high temperature resistant liquid coating). The externally coated cookware shall be subjected to thermal shock test as given in 8.7.1.’

Price Group 1

Amendment No.1 to IS 1660 : 2024

(Page 3, clause 8.8) — Substitute the following for the existing:

‘8.8 Requirements of PTFE, ceramic coating, powder coating, and high temperature resistant liquid coating are as follows:

The material shall not contain more than 0.05 percent as metal of any toxic metals such as lead, cadmium, mercury, arsenic or chromium (VI).

NOTE — Supplier certificate is acceptable.’

(Page 5, clause 11.1) — Substitute the following for the existing:

‘11.1 Each utensil shall have the following details:

- Capacity in litre/millilitre or size in cm/mm of utensil;
- Thickness of sheet (mm) or Classification;
- Material grade (for example, Lid-SS 304 or Aluminum as per IS 21, Body Aluminum as per IS 21);
- Manufacturer name or initials or trademark; and
- Batch number.

NOTES

1 The details can be marked in the form of a sticker/leaflet in case it cannot be stamped, embossed or etched.

2 For cooking utensils, (a), (b), (d), to be marked on utensils only, (c) and (e) can be marked on primary packaging.

3 For other utensils not used for cooking, (b) and (d) to be marked on utensils only, (a), (c), and (e) can be marked on primary packaging.

4 Details can also be put up on primary packaging for lid.

5 Details can be put on primary packaging for small utensils.’

[Page 17, Table 1, col (4)] — Substitute ‘Dia, D mm’ for ‘Dia, D (Inside) mm’.

(Page 17, Table 1, Note 1) — Substitute the following for the existing:

‘1 In case the groove (cut) is provided at the base of utensil, the depth of the groove shall not be more than 30 percent of the base thickness.’

(Page 18, Table 2) — Insert the following at the end:

‘Table 3 Cast Aluminium — Minimum Base Thickness of Body

(Clause 3.1.4)

Sl No.	Size mm	Heavy mm	Medium mm	Light mm
(1)	(2)	(3)	(4)	(5)
i)	Up to 120	2.0	1.6	1.2
ii)	121 to 300	2.5	2.0	1.5
iii)	301 to 350	3.0	2.50	2.0
iv)	351 and above	4.0	3.5	2.5

NOTE — Size can be diameter or sides.

(MED 33)

Publication, BIS, New Delhi