

AMENDMENT NO. 2 FEBRUARY 1976
TO
IS : 1676-1960 SPECIFICATION FOR
OLEIC ACID, TECHNICAL

Through this amendment a requirement and method of test for fluxing property of the material is being included in this standard on a request from the Ministry of Defence, Government of India. The amended standard, therefore, achieves full alignment with JSS:1076 Oleic acid, commercial (flux soldering) of Ministry of Defence.

Alteration

[Page 4 (page 5 of the reprint), Table I, clause reference under the title of the table]—Substitute '(Clauses 4.3 and 5.1)' for '(Clauses 4.2 and 5.1)'.

Addenda

[Page 3 (page 4 of the reprint), clause 4.1.1]—Add the following new clause after 4.1.1 and re-number the existing clause '4.2' as '4.3':

'4.2 Fluxing Property'—The material, when intended for Defence use, shall also pass the test prescribed in Appendix C.'

(Page 12, clause B-3.2.3)—Add the following new appendix after B-3.2.3:

A P P E N D I X C
(Clause 4.2)

TEST FOR FLUXING PROPERTY

C-1. OUTLINE OF THE METHOD

C-1.1 Material is applied to two properly cleaned test plates by brush and plates are put one over the other and soldered with soldering materials. The plates are then examined for any detachment.

C-2. MATERIALS

C-2.1 Tin Plates—two of 10 × 2.5 cm size.

C-2.2 Solvents—suitable, like acetone, carbon tetrachloride or toluene.

C-2.3 Solder Gun

C-2.4 Soldering Materials — suitable.

C-3. PROCEDURE

C-3.1 Take the tin plates and polish them with emery paper. De-grease them with a suitable solvent and finally clean with dry cloth.

C-3.2 Apply oleic acid by brush on the part of the surface of the plates to be soldered. Put the soldering material on the portion to be soldered and spray it by red hot solder gun. Put the plates one over the other and allow the soldered plates to cool for 2 to 3 minutes. The soldered portion shall not get detached under normal stress.

C-3.3 The test shall be taken as satisfactory if the plates do not get separated easily when tried to break off the soldered joint.

(CAFDC 5)