

AMENDMENT NO. 1 OCTOBER 1991
TO
IS 1727 : 1967 METHODS OF TEST FOR POZZOLANIC
MATERIALS
(First Revision)

(Page 6, clause 3.1) — Substitute the following for the existing clause :

3.1 Hydrated Lime — Standard hydrated lime supplied by National Council for Cement and Building Materials, New Delhi shall be used in the tests. The standard hydrated lime shall have the following composition

CaO	— 96 ± 0.5 percent
MgO	— 1 ± 0.5 percent
SiO ₂ , Max	— 1.0 percent
Insoluble residue, Max	— 1.0 percent

(Page 6, clause 3.2) — Substitute the following for the existing clause :

3.2 Cement — Cement for use in the tests shall be 33 grade ordinary Portland cement conforming to IS 269 : 1989.

(Page 6, clause 5.1.1) — Substitute 'IS 1070 : 1977' for 'IS 1070 : 1960'

(Page 6, foot-notes) — Delete foot-notes No. 2 and 3, and substitute

'Specification for 33 grade ordinary portland cement (fourth revision)' for 'Specification for ordinary rapid hardening and low heat Portland cement (revised)', and 'Specification for water for general laboratory use (second revision)' for 'Specification for water, distilled quality (revised)'

(Page 28, clause 9.7, Note) — Substitute the following for the existing note :

'NOTE — For curing the specimen at the specified relative humidity and temperature as given above, it is recommended that the controlled humidity and temperature chamber developed by National Council for Cement and Building Materials may be used for proper performance'

CED 2)