

**AMENDMENT NO. 2 JULY 2004
TO
IS 1767 : 1980 SPECIFICATION FOR
DICALCIUM PHOSPHATE FOR DENTIFRICE**

(Second Revision)

[Page 5, Table 1, Sl No. (iii), col 2] — Substitute the following for the existing:

‘Dicalcium phosphate (as CaHPO_4), percent by mass, *Min* (on dry basis) 98.0’

(Page 5, Table 1) — Insert the following at the end:

(1)	(2)	(3)	(4)
‘xvi)	Proteinous impurities	To pass test	A-17
xvii)	Reducing substances	To pass test	A-18’

(Page 15, clause A-16.3) — Include the following at the end:

A-17 TEST FOR PROTEINOUS IMPURITIES

A-17.1 Procedure

Heat 0.5 g of the material gently in a dry test tube. The material shall be taken to have passed the test, if no change in colour and no emission of any unpleasant odour is observed.

A-18 TEST FOR REDUCING SUBSTANCES

A-18.0 Outline of the Method

The colour produced with potassium permanganate is matched against that obtained with standard calcium carbonate solution.

A-18.1 Apparatus

A-18.1.1 Nessler Cylinders — 50-ml capacity.

A-18.2 Reagents

A-18.2.1 Concentrated Sulphuric Acid, 3 M.

A-18.2.2 Potassium Permanganate, 0.005 M.

Amend No. 2 to IS 1767 : 1980

A-18.2.3 *Calcium Carbonate (Analytical Grade)*

A-18.3 Procedure

Shake 1 g of the material with 5 ml of distilled water and 5 ml of 3 M Sulphuric acid for one minute, again add 20 ml of distilled water. Add 0.1 ml of 0.005 M potassium permanganate and shake for 15 s. Carry out a control test using 1 g of calcium carbonate in place of material and the same quantities of other reagents. Compare the colour produced in the two tubes.

A-18.3.1 The material shall be taken to have passed the test if the intensity of colour produced in the test with the material is not greater than that produced in the control test.

(PCD 19)