



AMENDMENT NO. 1 NOVEMBER 1985

TO

IS:1773-1982 SPECIFICATION FOR ELECTROPLATED  
COATINGS OF BRASS

*(First Revision)*

*(Page 5, clause 6.1)* - Add the following new  
clause after 6.1:

'6.1.1 To improve the quality of decorative brass plating on ferrous metals, it is now usual to apply an initial deposit of bright nickel or bright copper from a levelling type solution and then to brass plate, so that bright brass finish is obtained, without the need for the addition of brightner additives to the brass plating solution. Corrosion protection is provided by means of the initial nickel/copper deposit.'

(IMC 23)

---

Reprography Unit, ISI, New Delhi, India