

AMENDMENT NO. 1 NOVEMBER 1989
TO
IS : 1785 (PART 1) - 1983 SPECIFICATION
FOR PLAIN HARD-DRAWN STEEL WIRE
FOR PRESTRESSED CONCRETE
PART 1 COLD DRAWN STRESS-RELIEVED WIRE

(Second Revision)

(Page 4, Clause 3.2) — Substitute the following for the existing clause:

‘3.2 The wire rods obtained from the rolling mill shall be heat treated if required to make it suitable for cold drawing and thereafter the diameter of the wire rod shall be successively decreased to the required diameter by cold drawing it through a series of dies. The resultant wire shall by subjected to straightening and stress relieving process.’

(Page 7, clause 7.4) — Add the following at the end:

‘Alternatively, stress at 1.0 percent extension under load method as specified in 7.4.1 may be determined.’

(BSMDC 8)