

AMENDMENT NO. 3 APRIL 1997
TO
IS 1785 (Part 1) : 1983 SPECIFICATION FOR
PLAIN HARD-DRAWN STEEL WIRE FOR
PRESTRESSED CONCRETE
PART I COLD DRAWN STRESS-RELIEVED WIRE

(Second Revision)

(Page 4, clause 3.1.1, line 3) — Substitute '0.040 percent' for '0.050 percent'.

(Page 5, clause 5.1) — Delete the following values of Nominal Diameters and its corresponding values of Tolerances:

<i>Nominal Diameter</i> mm	<i>Tolerance</i> mm
3.00	± 0.04
2.50	± 0.025

[Page 5, clause 5.1.2 (see also Amendment No. 2)] — Delete the following values of Nominal Diameter and its corresponding values of Nominal Mass and Tolerance:

<i>Nominal Diameter</i> mm	<i>Nominal Mass</i> g/m	<i>Tolerance</i> g/m
3.00	55.5	± 1.5
2.50	38.5	± 1.25

(Page 6, clause 6.1) — Delete the following values of Nominal Diameter and its corresponding values of Tensile Strength:

<i>Nominal Diameter</i> mm	<i>Tensile Strength, Min</i> N/mm ²
2.50	2 010
3.00	1 865

Amend No. 3 to IS 1785 (Part 1) : 1983

(*Page 6, clause 6.4*) — Delete the following values of Nominal Diameter and its corresponding values of Elongation, Percent:

<i>Nominal Diameter</i> mm	<i>Elongation, Percent</i> Min
2.50	2.5
3.00	2.5

(*Page 8, clause 7.5*) — Delete the following values of Diameter of Wire and its corresponding values of Radius of Jaws:

<i>Diameter of Wire</i> mm	<i>Radius of Jaws</i> mm
2.50	7.50
3.00	10.00

(CED 54)