

AMENDMENT NO. 1 APRIL 1989

TO

**IS:1785(Part 2) - 1983 SPECIFICATION FOR
PLAIN HARD DRAWN STEEL WIRE FOR PRESTRESSED
CONCRETE**

PART 2 AS-DRAWN WIRE

(First Revision)

**(Page 5, clause 3.2, first sentence) -
Substitute the following for the existing sentence:**

'The wire rods obtained from the rolling mill shall be heat treated if required to make it suitable for cold drawing and thereafter the diameter of the wire rod shall be successively decreased to the required diameter by cold drawing it through a series of dies.'

(Page 6, clause 6.1) - Add the following note below the informal table:

'NOTE - In cases where the wires are likely to undergo further drawing, for example, in the case of prestressed concrete pipes, 10 percent reduction in tensile strength values specified above may be accepted by agreement between the purchaser and the manufacturer. In such cases, the bend test and/or torsion test requirements are also to be mutually agreed upon by the purchaser and the manufacturer.'

(Page 7, clause 7.4) - Add the following in the end:

'Alternatively, stress at 1.0 percent extension under load method as specified in 7.4.1 may be determined.'

(Page 7, clause 7.4.1) - Substitute the following for the first two sentences:

'When stress at 1.0 percent extension under load method is to be determined, an initial load corresponding to a stress of 196 N/mm^2 shall be applied to the test piece and a sensitive extensometer then attached.'

(BSMDC 8)