

AMENDMENT NO. 1 MARCH 2006
TO
IS 4270 : 2001 STEEL TUBES USED FOR WATER
WELLS — SPECIFICATION

(Third Revision)

(Page 1, clause 3.2) — Insert the following new clause after 3.2:

‘3.2.1 Random Length --- Normal manufacturing lengths, which may vary over a range.’

(Page 2, clauses 4 and 4.1) — Substitute the following for the existing clauses:

‘4.1 Types of Tubes — Steel tubes shall be manufactured through one of the following processes:

- a) Hot finished seamless (HFS);
- b) Cold finished seamless (CDS);
- c) Hot-finished welded (HFW); and
- d) Electric resistance welded or high frequency induction welded (ERW or HFIW).

NOTE — Tubes made by manual welding are not covered by this specification.’

(Page 4, Table 4) — Insert the following new sizes and the footnotes in Table 4 :

Nominal Bore of Pipe	Outside Diameter of Pipe	Thickness of Pipe	Mass of Plain Tube
mm	mm	mm	kg/m
300	323.9	12.0	92.30
350	355.6	12.0	101.67
350	355.6	14.0	117.93
600	609.6	14.0	205.6

NOTES

1 In case of drive casing pipes, of sizes 300 mm and above nominal bore of pipe, the length may be mutually agreed.

2 Mass of socketed tube shall be mutually agreed.

Amend No. 1 to IS 4270 : 2001

(*Tables 2, 3 and 5*) — Insert the following footnote under the tables:

‘NOTE — Mass of socketed tube shall be mutually agreed.’

(*Page 3, clause 7.2.4.1, line 3*) — Delete the word ‘specific’.

(*Page 8, clause 10.4*) — Insert the following new clause after 10.4:

‘10.5 For socket testing, the drift expansion shall be carried out on full length of the socket.’

(*Page 8, clause 11*) — Substitute the following for the existing clause:

‘For this test any two tubes may be screwed together till they butt, and their axes shall not then be out of line by more than 1.5 mm/m.’

(*Page 8, clause 14.1*) — Insert the following new clause after 14.1:

‘14.2 For ERW/HFIW pipes, the inner weld fin height shall not be more than 60 percent of the wall thickness.’

(*Page 8, Fig. 6*) — Delete.

(MTD 19)