

AMENDMENT NO. 1 JUNE 2005
TO
IS 4396 : 1981 SPECIFICATION FOR BARIUM
NITRATE FOR EXPLOSIVE AND PYROTECHNIC
COMPOSITIONS
(First Revision)

(Page 4, clause 2.2) — Insert the following subclause after the clause 2:

2.2.1 For defence purpose the sieving requirements are as follows:

<i>Sieving Requirements</i>	<i>Limit</i>
) Size 250 micrometre Retained on 250 micrometre IS sieve	Nil
) Size 250/125 micrometre	Nil
i) Retained on 250 micrometre IS sieve	Nil
ii) Retained on 125 micrometre IS sieve, percent by mass, <i>Min</i>	90
) Size 150 micrometre Retained on 150 micrometre IS sieve	Nil
) Size 125 micrometre Retained on 125 micrometre IS sieve	Nil
i Size 250 micrometre A	
i) Retained on 250 micrometre IS sieve	Nil
ii) Retained on 150 micrometre IS sieve, percent by mass, <i>Max</i>	50
Size 125 micrometre A	
i) Retained on 180 micrometre IS sieve	Nil
ii) Retained on 125 micrometre IS sieve, percent by mass, <i>Max</i>	10
iii) Retained on 63 micrometer IS sieve, percent by mass	50 <i>Min</i> 70 <i>Max</i>

Amend No. 1 to IS 4396 : 1981

<i>Sieving Requirements</i>	<i>Limit</i>
g) Size 150/90 micrometre A	
i) Retained on 150 micrometre IS sieve	Nil
ii) Retained on 90 micrometre IS sieve, percent, <i>Min</i>	50