

AMENDMENT NO. 2 MAY 2024
TO
IS 4454 (PART 4) : 2001 STEEL WIRE FOR MECHANICAL SPRINGS —
SPECIFICATION
PART 4 STAINLESS STEEL WIRE
(Second Revision)

(Page 4, Table 4) — Substitute the following for the existing table:

Table 4 Tensile Strength for Stainless Steel Spring Wire

(Clause 10.1.1)

Wire Diameter (Nominal), mm		Tensile Strength for Grades, MPa, <i>Min</i>			Reduction of Area after Fracture Percentage, <i>Min</i>
Over	Up to and Including	Grade 1	Grade 2	Grade 3	
(1)	(2)	(3)	(4)	(5)	(6)
—	0.20	2 150	2 000	1 720	—
0.20	0.30	2 050	1 975	1 700	—
0.30	0.40	2 050	1 925	1 670	—
0.40	0.50	1 950	1 900	1 650	—
0.50	0.65	1 900	1 850	1 620	—
0.65	0.80	1 850	1 800	1 600	—
0.80	1.00	1 850	1 775	1 570	—
1.00	1.25	1 750	1 725	1 550	40
1.25	1.50	1 700	1 675	1 500	40
1.50	1.75	1 650	1 625	1 450	40
1.75	2.00	1 650	1 575	1 400	40
2.00	2.50	1 550	1 525	1 350	40
2.50	3.00	1 450	1 475	1 300	40
3.00	3.50	1 450	1 425	1 250	40
3.50	4.25	1 450	1 400	1 225	40
4.25	5.00	1 350	1 350	1 200	40
5.00	6.00	1 350	1 300	1 150	40
6.00	7.00	1 270	1 250	1 125	40
7.00	8.50	1 130	1 200	1 075	40
8.50	10.00	980	1 175	1 050	40

NOTES

1 1 MPa = 1 N/mm² = 1 MN/m² = 0.102 0 kgf/mm².

2 The maximum tensile strength shall be the minimum value plus 15 percent of the minimum value.

3 The wire is supplied in cold drawn condition. The tensile strength in the finished spring may be substantially influenced by a heat treatment.

Price Group 1

Amendment No. 2 to IS 4454 (Part 4) : 2001

(Page 5, clause **15.1.1**) — Delete.

(Page 5, clause **15.1**) — Insert the following new clause after **15.1**:

‘15.2 BIS Certification Marking

The product(s) conforming to the requirements of this standard may be certified as per the conformity assessment schemes under the provisions of the *Bureau of Indian Standards Act, 2016* and the Rules and Regulations framed thereunder, and the product(s) may be marked with the Standard Mark.’