

**AMENDMENT NO. 1 MAY 2002
TO
IS 4454 (PART 4) : 2001 STEEL WIRES FOR
MECHANICAL SPRINGS – SPECIFICATION
PART 4 STAINLESS STEEL WIRE**

(Second Revision)

(Page 6, Table 5) — Substitute the following table for the existing:

Table 5 Reference Data for the Modulus of Elasticity and Rigidity

Steel Grade	Modulus of Elasticity MPa		Modulus of Rigidity MPa	
	Untempered	Tempered	Untempered	Tempered
(1)	(2)	(3)	(4)	(5)
1	185 000	195 000	70 000	73 000
2	185 000	195 000	70 000	73 000
3	1 80 000	190 000	68 000	71 000

(MTD 4)