

AMENDMENT NO. 1 AUGUST 1978

TO

IS:4492-1968 SPECIFICATION FOR WELDED
V-BLOCKS (DIAMETER RANGE 300 TO 2 000 mm)

Alterations.

(*Page 8, clause 6.2, first sentence*) –
Substitute the following for the existing
sentence:

' The flanks of vee shall be hardened to
54 to 58 *HRC* (*see* IS:1586-1968⁺). '

(*Page 8, foot-note with '+' mark*) -
Substitute the following for the existing
foot-note:

' + Method for rockwell hardness test (B and
C scales) for steel (*first revision*) . '

(EDC 43)