

AMENDMENT NO. 1 MARCH 2014
TO
IS 15907 : 2010 AGRO TEXTILES — HIGH DENSITY
POLYETHYLENE (HDPE) WOVEN BEDS FOR
VERMICULTURE — SPECIFICATION

(Page 1, clause 4.2) — Substitute the following for the existing:

‘4.2 HDPE Fabric

Beds shall be manufactured by using suitable HDPE woven fabric (see IS 6899) so that finished bed meets the requirements given in Table 1 and 5.1 to 5.4.’

(Page 1, clauses 4.3, 4.3.1 and 4.3.2) — Delete and renumber clause 4.4 as 4.3.

(Page 1, clause 5.1) — Insert the following new clause after 5.1 and renumber the subsequent clauses::

‘5.2 Lamination

5.2.1 The fabric shall be laminated with the low density polyethylene (LDPE) or suitable combination of LDPE and linear low density polyethylene (LLDPE) melt of coating grade on each side having thickness not less than 25 microns and the coating shall be suitable UV stabilized by incorporating UV stabilizer (see Note under 4.1). The coating thickness shall be measured at a pressure of 2 ± 0.01 kPa by method A of IS 13162 (Part 3). The coating film along with colour master batch to get the desired shade shall be such that the finished bed meets the requirements of UV stability and colour fastness to light as given in Table 1.

5.2.2 A 7-layer laminated fabric is produced using a combination of 3-layers of HDPE fabric and 4-layers of coating film. The layers of HDPE fabric used to manufacture beds shall be joined by sandwich lamination. The lamination as given above shall be such that the finished bed meets the requirements given in Table 1. The minimum coating thickness of the sandwich lamination shall be 40 μ . The coating thickness shall be measured at a pressure of 2 ± 0.01 kPa by method A of IS 13162 (Part 3).’

Amendment No. 1 to IS 15907 : 2010

(Page 4, Table 1, Heading) — Substitute the following for the existing:

‘Table 1 Requirements of Beds Made from HDPE Woven Fabrics
(Clauses 4.1, 4.2, 5.2.1, 5.2.2 and 6)’

(Page 5, Annex A) — Insert the following reference at appropriate place:

<i>IS No.</i>	<i>Title</i>
13162 (Part 3) : 1992	Geotextiles — Methods of test : Part 3 Determination of thickness at specified pressures