

AMENDMENT NO. 2 MARCH 2015
TO
IS 15907 : 2010 AGRO TEXTILES — HIGH DENSITY POLYETHYLENE (HDPE)
WOVEN BEDS FOR VORMICULTURE — SPECIFICATION

[Page 1, clause 5.3.1 (see also Amendment No. 1)] — Substitute the following for the existing:

‘5.3.1 The bed shall be constructed by heat sealing laminated pieces of woven fabric of the desired dimensions. The panels shall be flat (overlap) joined. The top edges of the bed shall be hemmed by heat sealing along with a jute/sisal rope of minimum 6 mm diameter placed inside the hem as reinforcement. The width of the hem shall be minimum 40 mm. Three net windows of size 260 mm × 150 mm each with a tolerance of ±20 mm shall be provided on both sides of the bed along the length for ventilation. These windows shall be made of polyethylene nets and shall be heat sealed at equidistance along the periphery of the bed as shown in Fig. 1. An outlet of 40 mm × 100 mm with a tolerance of ± 10 mm at the bottom in one corner shall also be provided for draining out the liquor produced during the process of composting. This outlet shall be covered by polyethylene nets and shall be heat sealed.’

[Page 2, clause 5.3.2, sentence 4 (see also Amendment No. 1)] — Substitute the following for the existing:

‘The pockets shall have a finished width of 120 mm minimum.’

(Page 2, clause 6.1) — Substitute the following for the existing:

‘6.1 Dimensions and Mass

The dimensions of the bed shall be 3 600 mm (*L*) × 1 200 mm (*W*) × 600 mm (*H*). The following tolerance shall be permissible for length, width, height and mass (g/m²):

<i>Dimension</i>	<i>Tolerance</i> Percent	
Length	+ 5 – 2	
Width	+ 5 – 2	
Height	+ 5 – 2	
Mass (g/m ²)	+ 6 – 2	on declared mass subject to minimum mass of 340 g/m ² ’