

AMENDMENT NO. 2 JULY 2024
TO
IS 15997 : 2012 LOW NICKEL AUSTENITIC STAINLESS STEEL SHEET AND
STRIP FOR UTENSILS AND KITCHEN APPLIANCES — SPECIFICATION

(First cover page, Hindi title) — Substitute ‘बर्तनो और रसोईघर साधित्रों के लिए अल्प निकल ऑस्टेनिटिक स्टेनलेस इस्पात की प्लेट, चादर और पत्ती — विशिष्टि’ for ‘बर्तनो एवं रसोईघर साधित्रों के लिए अल्प निकल ऑस्टेनिटिक स्टेनलेस स्टील की चादर एवं पत्ती — विशिष्टि’.

(First cover page, English title) — Substitute ‘Low Nickel Austenitic Stainless Steel Plate, Sheet and Strip for Utensils and Kitchen Appliances — Specification’ for ‘LOW NICKEL AUSTENITIC STAINLESS STEEL SHEET AND STRIP FOR UTENSILS AND KITCHEN APPLIANCES — SPECIFICATION’.

(Page 1, Title) — Substitute ‘LOW NICKEL AUSTENITIC STAINLESS STEEL PLATE, SHEET AND STRIP FOR UTENSILS AND KITCHEN APPLIANCES — SPECIFICATION’ for ‘LOW NICKEL AUSTENITIC STAINLESS STEEL SHEET AND STRIP FOR UTENSILS AND KITCHEN APPLIANCES — SPECIFICATION’.

(Page 1, clause 2) — Delete the following:

‘1387 : 1993 General requirements for the supply of metallurgical materials (second revision)’.

(Page 1, clause 2) — Insert the following reference at appropriate place:

‘IS 8910 : 2022/ Steel and steel products — General technical delivery requirements (second revision)’.
ISO 404 : 2013

(Page 1, clause 4.1) — Substitute ‘IS 8910’ for ‘IS 1387’.

(Page 1, clause 4.2) — Substitute the following for the existing:

‘Steels covered by the standard shall be ordered and delivered on the basis of the following:

- a) Chemical composition (only for hot-rolled steels);
- b) Chemical composition and mechanical properties in the annealed condition; and
- c) Chemical composition and mechanical properties, in any other condition as agreed to between the purchaser and the supplier.’

(Page 1, clause 4.2) — Insert the following new clause at the end:

‘4.3 Information to be Given by the Purchaser

4.3.1 Basis for Order

While placing an order for the purchase of material covered by this standard, the purchaser should specify the following:

- a) Grade designation;
- b) Form (plate, sheet or strip);
- c) Nominal dimensions — Thickness, width and length (for cut length);
- d) Condition (hot rolled, cold rolled, annealed);
- e) Surface finish (see 11);
- f) Edge condition (see 13); and

Price Group 3

Amendmnet No. 2 to IS 15997 : 2012

g) Method of manufacture, if any specified.'

(Page 1, clause 7) — Substitute the following for the existing:

'Unless otherwise mutually agreed to between the purchaser and the supplier, the material shall be supplied in annealed condition.'

(Page 2, clause 9.3) — Insert the following at the end of the clause:

'For conditions other than those mentioned in Table 3, the mechanical properties shall be mutually agreed to between the purchaser and the supplier.'

(Page 3, Table 4) — Substitute the following for the existing:

Table 4 Surface Finish

(Clause 11)

SI No.	Condition	Finish	Description	Remarks
(1)	(2)	(3)	(4)	(5)
i)	Hot rolled	a) No. 0	Hot rolled and/or annealed	Suitable only for certain heat resisting applications where surface is not important, presence of scale impairs resistance to corrosion. Surface inspection is not practicable and fool proof
		b) No. 1	Hot rolled, annealed and descaled (pickled)	Generally used for industrial application where heat and corrosion resistance is more important and smoothness and uniformity of finish are not important. Repair grinding marks may be present in local areas
ii)	Cold rolled	a) 2D	Cold rolled, annealed and descaled (pickled)	A dull, smooth and uniform surface finish most suited for deep drawing applications
		b) 2B	Cold rolled, annealed, descaled (pickled) and skin passed	A smoother and brighter surface finish (as compared to 2D) most suitable for general applications
		c) BA	Cold rolled, bright in protective atmosphere	A cold rolled reflective surface finish. Suitable for applications demanding bright and lustrous surface
		d) No. 3	Coarse grit polished surface finish	A uniform polished surface finish obtained with coarse abrasives of 100 to 120 grit on one or both surfaces. Suitable for use as a finish polished surface such as for panelling or any other application requiring such surface finish
		e) No. 4	Standard polished surface finish	A standard uniform polished surface finish produced with abrasives of 120 to 150 grit size and the finish is finer than No. 3 finish. Suitable for general purpose polished finish used for panelling, appliances, equipment and architectural applications

Amendmnet No. 2 to IS 15997 : 2012

(Page 3, clause 12) — Substitute the following for the existing:

‘12 DIMENSIONS

Unless otherwise agreed to between the manufacturer and the purchase, dimensions of plate, sheet and strip shall be as follows:

Thickness : 0.20 mm to 50 mm; and

Width : upto 2 000 mm.’

(Page 3, Table 5) — Substitute the following for the existing:

Table 5 Permissible Variations in Thickness for Hot-Rolled Product

(Clause 14.1)

All dimensions in millimetres.

Sl No.	Thickness	Tolerance on Thickness for Width			
		< 1 000	1 000 to < 1 250	1 250 to < 1 600	1 600 to ≤ 2 000
(1)	(2)	(3)	(4)	(5)	(6)
i)	1.00 to < 1.50	± 0.15	± 0.15	± 0.20	± 0.25
ii)	1.50 to < 2.00	± 0.20	± 0.20	± 0.25	± 0.30
iii)	2.00 to < 2.50	± 0.20	± 0.25	± 0.30	± 0.35
iv)	2.50 to < 3.00	± 0.25	± 0.30	± 0.30	± 0.40
v)	3.00 to < 4.00	± 0.30	± 0.30	± 0.35	± 0.45
vi)	4.00 to < 5.00	± 0.40	± 0.40	± 0.45	± 0.60
vii)	5.00 to < 6.00	± 0.50	± 0.50	± 0.55	± 0.70
viii)	6.00 to < 8.00	± 0.60	± 0.60	± 0.60	± 0.75
ix)	8.00 to < 10.00	± 0.65	± 0.65	± 0.65	± 0.80
x)	10.00 to < 16.00	± 0.70	± 0.70	± 0.70	± 0.85
xi)	16.00 to < 25.00	± 0.80	± 0.80	± 0.80	± 0.95
xii)	25.00 to < 40.00	± 0.90	± 0.90	± 0.90	± 1.10
xiii)	40.00 to < 50.00	± 1.00	± 1.00	± 1.00	± 1.20

NOTES

1 Thickness measurements are taken at least 15 mm from the edge of the product in case of trimmed edges atleast 25 mm from the edge of the product in case of mill edge.

2 For width > 2 000 mm, tolerances on thickness shall be agreed to between the purchaser and the manufacturer/the seller.

3 For thickness ≥ 50 mm, tolerances on thickness shall be agreed to between the purchaser and the manufacturer/the seller.

4 In case of wide strip of hot rolled coils, the specified values for tolerances shall not apply to mill edge of the coil for total length (l). Which is calculated using the formula: $l(m) = 90/\text{nominal thickness in mm}$, with maximum total length (both ends) of 20 m per coil.

Amendmnet No. 2 to IS 15997 : 2012

(Page 4, Table 6) — Substitute the following for the existing:

Table 6 Permissible Variations in Thickness for Cold-Rolled Product

(Clause 14.1)

All dimensions in millimetres.

SI No.	Thickness	Tolerance on Thickness for Width			
		< 1 000	1 000 to < 1 250	1 250 to < 1 600	1 600 to ≤ 2 000
(1)	(2)	(3)	(4)	(5)	(6)
i)	From 0.20 to < 0.30	± 0.04	± 0.04	—	—
ii)	From 0.30 to < 0.40	± 0.05	± 0.05	± 0.05	—
iii)	From 0.40 to < 0.60	± 0.08	± 0.08	± 0.08	—
iv)	From 0.60 to < 0.80	± 0.10	± 0.10	± 0.10	—
v)	From 0.80 to < 1.25	± 0.12	± 0.15	± 0.15	± 0.15
vi)	From 1.25 to < 1.50	± 0.13	± 0.15	± 0.20	± 0.20
vii)	From 1.50 to < 2.00	± 0.15	± 0.20	± 0.20	± 0.20
viii)	From 2.00 to < 2.50	± 0.20	± 0.20	± 0.25	± 0.25
ix)	From 2.50 to < 3.00	± 0.25	± 0.25	± 0.30	± 0.30
x)	From 3.00 to < 4.00	± 0.30	± 0.30	± 0.35	± 0.35
xi)	From 4.00 to < 5.00	± 0.35	± 0.35	± 0.40	± 0.40

NOTES

1 For width > 2 000 mm, tolerances on thickness shall be agreed to between the purchaser and the manufacturer/the seller.

2 Tolerances on thickness which are not mentioned in the above table shall be agreed to between the purchase and the manufacturer/the seller.

3 For thickness of 5 mm and above, the tolerance shall be agreed as between the purchase and the manufacturer/the seller.

(Page 4, Table 7) — Substitute the following for the existing:

Table 7 Permissible Variations in Width for Mill Edge in Hot and Cold Rolled Product

(Clause 14.2.1)

All dimensions in millimetres.

SI No.	Width	Tolerance on Width	
		Plus	Minus
(1)	(2)	(3)	(4)
i)	< 250	5	0
ii)	≥ 250, < 500	20	0
iii)	≥ 500, < 1 000	30	0
iv)	≥ 1 000, ≤ 2 000	35	0

NOTES

1 For width > 2 000 mm, tolerances on width shall be agreed to between the purchaser and the manufacturer/supplier.

2 In case of wide strip of hot rolled coils, the specified values for tolerances shall not apply to mill edge of the coil for total length (l). Which is calculated using the formula $l(m) = 90/\text{nominal thickness in mm}$, with maximum total length (both ends) of 20 m per coil.

Amendmnet No. 2 to IS 15997 : 2012

(Page 4, Table 8) — Substitute the following for the existing:

Table 8 Permissible Variations in Width for Trimmed Edge Hot-Rolled Product

(Clause 14.2.2)

All dimensions in millimetres.

SI No.	Width	Tolerance on Width	
		Plus	Minus
(1)	(2)	(3)	(4)
i)	$\leq 2\ 000$	5	0

NOTE — For width > 2 000 mm, tolerances on width shall be agreed to between the purchaser and the manufacturer.

(Page 4, Table 9) — Substitute the following for the existing:

Table 9 Permissible Variations in Width for Trimmed Edge Cold Rolled Product for Cold Rolled Strip in Coils and Cut Lengths

(Clause 14.2.2)

All dimensions in millimetres.

SI No.	Thickness	Tolerance on Width				
		< 250	250 to < 500	500 to < 1 000	1 000 to < 1250	1 250 to $\leq 2\ 000$
(1)	(2)	(3)	(4)	(5)	(6)	(7)
i)	< 0.6	± 0.20	± 0.30	± 0.50	± 1.00	± 1.00
ii)	From 0.6 to < 1.00	± 0.25	± 0.30	± 0.50	± 1.00	± 1.00
iii)	From 1.00 to < 1.50	± 0.30	± 0.40	± 0.60	± 1.20	± 1.20
iv)	From 1.50 to < 2.50	± 0.40	± 0.50	± 0.70	± 1.40	± 1.40
v)	From 2.50 to < 4.00	± 0.40	± 0.50	± 0.80	± 1.60	± 1.60
vi)	From 4.00 to < 5.00	± 0.50	± 0.70	± 1.00	± 2.00	± 2.00

NOTES
1 For thickness of 5 mm and above, tolerances shall be agreed to between the purchaser and the manufacturer/the seller.
2 For width > 2 000 mm, tolerances on width shall be agreed to between the purchaser and the manufacturer/supplier.

(Page 5, clause 17.2) — Substitute the following for the existing:

‘17.2 BIS Certification Marking

The product(s) conforming to the requirements of this standard may be certified as per the Conformity assessment schemes under the provisions of the *Bureau of Indian Standards Act, 2016* and the Rules and Regulations framed thereunder, and the product(s) may be marked with the Standard Mark.’

(Page 5, clause 17.2.1) — Delete.