

AMENDMENT NO. 3 JUNE 2025

TO

IS 15997 : 2012 LOW NICKEL AUSTENITIC STAINLESS STEEL PLATE, SHEET AND STRIP FOR UTENSILS AND KITCHEN APPLIANCES — SPECIFICATION

(Page 1, clause 2) — Insert the following entry at appropriate place:

‘IS No.

Title

IS 14650 : 2023 Unalloyed and alloyed steel ingot and semi-finished products for re-rolling purposes —
Specification (first revision)’

(Page 1, clause 5) — Insert the following at the end:

‘Steels used for manufacturing the product covered in the standard shall conform to the requirements of
IS 14650.’

(Page 2, Table 1) — Substitute the following for the existing:

‘Table 1 Chemical Composition

(Clauses 8.1, 8.1.1 and 10.1)

Sl No.	Grade Designation		Constituents, Percent								
	[See IS 1762 (Part 1)]	Numerical Symbol	C, Max	Si, Max	Mn	Ni	Cr	S, Max	P, Max	Cu	N
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(10)	(12)
i)	X10Cr15Mn9 Cu2Ni1N	N1	0.12	0.75	8.5 to 10.5	1 to 2	14.5 to 16.0	0.03	0.08	1.5 to 2.5	0.08 to 0.2
ii)	X8Cr16Mn8 Cu2Ni2N	N2	0.10	1.00	6.5 to 9.0	1.5 to 3.5	15.5 to 17.0	0.03	0.07	2 to 4	0.10 to 0.25
iii)	X8Cr16Mn7 Cu2Ni4N	N3	0.09	0.75	6 to 8	4 to 6	16.0 to 17.5	0.03	0.07	1.5 to 2.5	0.05 to 0.15
iv)	X06Cr15Mn10 Cu2NiN	N5	0.12	1.0	9.5 to 11.5	0.45 to 0.95	14.0 to 16.5	0.03	0.10	1.5 to 2.5	0.10 to 0.25
v)	X06Cr14Mn10 Cu1NiN	N6	0.12	1.0	9.25 to 11.50	0.25 to 0.95	13.5 to 16.0	0.03	0.10	1.0 to 2.0	0.10 to 0.25
vi)	X07Cr14Mn1 0CuNiN	N7	0.14	1.0	9.0 to 11.5	0.20 to 0.95*	13.5 to 16.0	0.03	0.10	0.4 to 0.8	0.10 to 0.25
NOTE — Elements not specified shall not be intentionally added to the steel without the agreement of purchaser except for the finish of the cast. All precautions must be taken to avoid addition of elements from scrap metal and raw material used in production of elements likely to affect Mechanical characteristics as well as the suitability for use of steel for utensils.											

*Stainless steel of Grade N7 may be supplied with Ni content 0.20 to 1.25, if agreed to between the manufacturer and the purchaser.’

(MTD 16)

Price Group 1
Publication, BIS, New Delhi