

AMENDMENT NO. 1 MARCH 2023

TO

IS 15997 : 2012 LOW NICKEL AUSTENITIC STAINLESS STEEL SHEET AND STRIP FOR UTENSILS AND KITCHENAPPLIANCES — SPECIFICATION

[Page 2, Table 1, Sl No. (iii)] — Insert the following new grades in the existing table at the end:

iv)	X06Cr15Mn10 Cu2NiN	N5	0.12	1.0	9.5 - 11.5	0.45 - 0.95	14.0 - 16.5	0.030	0.10	1.5 - 2.5	0.10 - 0.25
v)	X06Cr14Mn10 Cu1NiN	N6	0.12	1.0	9.25 - 11.5	0.25 - 0.95	13.5 - 16.0	0.030	0.10	1.0 - 2.0	0.10 - 0.25
vi)	X07Cr14Mn1 0CuNiN	N7	0.14	1.0	9.0 - 11.5	0.20 - 0.95	13.5 - 16.0	0.030	0.10	0.4 - 0.8	0.10 - 0.25

[Page 2, Table 3, Sl No. (iii)] — Insert the following at the end:

iv)	X06Cr15Mn10Cu2 NiN	N5	350	700	40
v)	X06Cr14Mn10Cu1 NiN	N6	375	750	40
vi)	X07Cr14Mn10Cu NiN	N7	400	800	30

‘NOTE — During the tensile testing for grades N5, N6 and N7, in case fracture takes place outside the gauge length, re-testing shall be done for the cases in which specified minimum elongation is not achieved.’