

**AMENDMENT NO. 1 AUGUST 2023**  
**TO**  
**IS 16008 (PART 2) : 2016 AGRO TEXTILES — SHADE NETS FOR AGRICULTURE**  
**AND HORTICULTURE PURPOSES — SPECIFICATION**  
**PART 2 SHADE NETS MADE FROM MONO FILAMENT YARNS**  
( *First Revision* )

(Page 1, clause 4.1, sentence 2) — Substitute the following for the existing sentence:

‘The linear density of the monofilament yarn shall be 33.33 tex (300 denier) for Type I, Type II and Type II A shade nets and 55.55 tex (500 denier) for Type III and Type IV shade nets.’

(Page 1, clause 5) — Substitute the following for the existing:

‘Based on the shading percentage, the monofilament agro shade nets are classified as follows:

- a) Type I — having shading percentage of 35 percent;
- b) Type II and Type II A — having shading percentage of 50 percent;
- c) Type III — having shading percentage of 75 percent; and
- d) Type IV — having shading percentage of 90 percent.’

(Page 2, clause 6.1) — Substitute the following informal table for the existing:

| <i>Dimension</i>       | <i>Tolerance,<br/>percent</i> |
|------------------------|-------------------------------|
| Length                 | + 5<br>– 0                    |
| Width                  | + 3<br>– 0                    |
| Mass, g/m <sup>2</sup> | + 6<br>– 0                    |

(Page 2, Table 1) — Substitute the table for the existing:

**Table 1 Requirements of Shade Nets Made from Monofilament Yarns**

(Clause 6.2)

| SI No. | Characteristic(s)                                                                                                                  | Requirement(s) |         |           |          |         | Method of Test, Ref to |
|--------|------------------------------------------------------------------------------------------------------------------------------------|----------------|---------|-----------|----------|---------|------------------------|
|        |                                                                                                                                    | Type I         | Type II | Type II A | Type III | Type IV |                        |
| (1)    | (2)                                                                                                                                | (3)            | (4)     | (5)       | (6)      | (7)     | (8)                    |
| i)     | Mass, g/m <sup>2</sup> , <i>Min</i>                                                                                                | 95             | 125     | 105       | 310      | 460     | IS 1964                |
| ii)    | Average Breaking Strength of shadenets fabric (Strip method, 325 mm × 50 mm test piece with gauge length of 200 mm), <i>N, Min</i> |                |         |           |          |         | IS 1969 (Part 1)       |
|        | a) warpway                                                                                                                         | 300            | 300     | 300       | 450      | 650     |                        |
|        | b) weftway                                                                                                                         | 350            | 620     | 620       | 1 700    | 4 300   |                        |

**Price Group 1**

**Amendment No. 1 to IS 16008 (Part 2) : 2016**

**Table 1 (Concluded)**

| Sl No. | Characteristic(s)                                               | Requirement(s)                            |             |             |             |             | Method of Test, Ref to               |
|--------|-----------------------------------------------------------------|-------------------------------------------|-------------|-------------|-------------|-------------|--------------------------------------|
|        |                                                                 | Type I                                    | Type II     | Type II A   | Type III    | Type IV     |                                      |
| (1)    | (2)                                                             | (3)                                       | (4)         | (5)         | (6)         | (7)         | (8)                                  |
| iii)   | Retention of breaking strength after UV exposure, N, <i>Min</i> | ← 85 Percent of original value (fabric) → |             |             |             |             | Annex B and IS 1969 (Part 1)         |
| iv)    | Colour fastness to artificial light <sup>1)</sup>               | 4 or better                               | 4 or better | 4 or better | 4 or better | 4 or better | IS 2454                              |
| v)     | Bursting pressure, kgf/cm <sup>2</sup> , <i>Min</i>             | 11                                        | 13          | 13          | 30          | 40          | IS 1966 (Part 1)<br>IS 1966 (Part 2) |
| vi)    | Shading percentage                                              | 30 to 40                                  | 45 to 55    | 45 to 55    | 70 to 80    | 85 to 95    | Annex C                              |

<sup>1)</sup>Applicable for coloured shade nets only

(Page 4, clause **B-2.2**) — Substitute the following for the existing:

**‘B-2.2** The duration of the test shall be 1 500h.’

(TXD 35)

Publication, BIS, New Delhi