

AMENDMENT NO. 2 APRIL 2017
TO
IS 16098 (PART 2) : 2013 STRUCTURED-WALL PLASTICS PIPING SYSTEMS FOR
NON-PRESSURE DRAINAGE AND SEWERAGE — SPECIFICATION

PART 2 PIPES AND FITTINGS WITH NON-SMOOTH EXTERNAL SURFACE, TYPE B

(Page 3, clause 4, e_4) — Insert the following after e_4 :

‘ e_5 – wall thickness of the inside layer under a hollow section’

(Page 5, Table 4, title) — Substitute ‘**Table 4 Material Characteristics for PP Material in Pipe Form**’ for the existing title.

[Page 11, clause 8.1.1, Table 10, Sl No.(ii), col (4), Sl No. 6] — Substitute ‘ $250 < d_{im,Max} \leq 315$ ’ for ‘ $200 < d_{im,Max} \leq 315$ ’.

[Page 12, clause 9, Table 12, Sl No. (i)] — Substitute the following for the existing:

Table 12

Sl No.	Characteristics	Requirements	Test Parameters	Method of Test, Ref to	
				Annex	IS
(1)	(2)	(3)	(4)	(5)	(6)
i)	Tightness of elastomeric ring seal joint	a) No leakage	a) Temperature	: $27 \pm 2^\circ\text{C}$	12235 (Part 8/ Sec 2 and Sec 3)
			b) Joint deflection for:		
			1) $d_e \leq 315$ mm	: 2°	
			2) $315 \text{ mm} < d_e \leq 630$ mm	: 1.5°	
			3) $630 \text{ mm} < d_e$	: 1°	
		b) No leakage	c) Water pressure maintained for duration of 15 minutes	: 5 kPa (0.05 bar)	
			Water pressure maintained for duration of 15 minutes	: 50 kPa (0.5 bar)	
		c) ≤ -27 kPa (–0.27 bar)	Air pressure	: -30 kPa (–0.3 bar)	

[Page 13, clause 10.2.1, Table 17, Sl No. (i), col (2)] — Substitute the following for the existing:

‘Resistance to internal hydrostatic pressure for 140 h at 4.2 MPa’.

[Page 36, clause G-6.2.1.2 (e)] — Substitute the following for the existing: ‘Return to (a)’.